



Designation: D7812 – 22

Standard Test Method for Tensile Testing of Aramid Paper¹

This standard is issued under the fixed designation D7812; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the tensile testing of aramid paper with thickness less than 1 mm. This test method includes testing procedures only and includes no specifications or tolerances.

1.2 The procedures given in this test method are for use with computer-controlled constant-rate-of-elongation tensile testing equipment.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- D76 Specification for Tensile Testing Machines for Textiles
- D123 Terminology Relating to Textiles
- D202 Test Methods for Sampling and Testing Untreated Paper Used for Electrical Insulation
- D374M Test Methods for Thickness of Solid Electrical Insulation (Metric) (Withdrawn 2016)³
- D1776 Practice for Conditioning and Testing Textiles

¹ This test method is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.19 on Industrial Fibers and Metallic Reinforcements.

Current edition approved Nov. 1, 2022. Published December 2022. Originally approved in 2016. Last previous edition approved in 2016 as D3512 – 16. DOI: 10.1520/D7812-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

- D4848 Terminology Related to Force, Deformation and Related Properties of Textiles
- D6477 Terminology Relating to Tire Cord, Bead Wire, Hose Reinforcing Wire, and Fabrics
- E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method
- E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods

3. Terminology

3.1 *Definitions*—The following terms are relevant to this standard: aramid paper, breaking force, elongation, initial modulus, tensile strength, and Tensile Energy Absorption.

3.1.1 For definitions of terms related to industrial fibers and metallic reinforcements, refer to Terminology D6477.

3.1.2 For definitions of terms related to force and deformation in textiles, refer to Terminology D4848.

3.1.3 For definitions of other terms related to textiles, refer to Terminology D123.

4. Summary of Test Method

4.1 A conditioned sample of aramid paper is clamped in a tensile testing machine and then stretched or loaded until broken.

4.2 The output of a constant-rate-of-extension (CRE) tensile testing machine can be connected with electronic recording and computing equipment, which may be programmed to calculate and print the test results of tensile properties of interest.

4.3 Breaking force and elongation are determined directly. Modulus and Tensile Energy Absorption are calculated from the force-elongation curve.

5. Significance and Use

5.1 The levels of tensile properties obtained when testing aramid paper are dependent on the age and history of the specimen and on the specific conditions used during the test. Among these conditions are rate of stretching, type of clamps, gauge length of specimen, temperature and humidity of the atmosphere, rate of airflow across the specimen, and temperature and moisture content of the specimen. Testing conditions accordingly are specified precisely to obtain reproducible test results on a specific sample.

5.2 Tensile strength is used in engineering calculations when designing various types of products.

5.3 Elongation of the paper is taken into consideration in the design and engineering of reinforced products because of its effect on uniformity of the finished product and its dimensional stability during service.

5.4 Stiffness is a measure of the resistance of the paper to extension as a force is applied.

5.5 Tensile Energy Absorption is dependent on the relationship of force to elongation. It is a measure of the ability of a textile structure to absorb mechanical energy. Tensile Energy Absorption is work-to-break per area.

5.6 It should be emphasized that, although the preceding parameters are related to the performance of the product, the actual configuration of the product is significant. Shape, size, and internal construction also can have appreciable effects on product performance. It is not possible, therefore, to evaluate the performance of the end product in terms of the reinforcing material alone.

5.7 If there are differences of practical significance between reported test results for two laboratories (or more), comparative tests should be performed to determine if there is a statistical bias between them, using competent statistical assistance. As a minimum, test samples should be used that are as homogeneous as possible, that are drawn from the material from which the disparate test results were obtained, and that are randomly assigned in equal numbers to each laboratory for testing. Other materials with established test values may be used for this purpose. The test results from the two laboratories should be compared using a statistical test for unpaired data, at a probability level chosen prior to the testing series. If a bias is found, either its cause must be found and corrected, or future test results must be adjusted in consideration of the known bias.

6. Apparatus

6.1 *Thickness*—Micrometer, conforming to the specifications as given in Test Method [D374M](#).

6.2 *Grammage*—Weighing device, readable and accurate to within 0.25 % of the applied load. When in use, the weighing device shall be shielded from air currents.

6.3 *Tensile Testing Machine*—A single-strand tensile testing machine of the constant rate of extension (CRE) type. The specifications and methods of calibration and verification of these machines shall conform to Specification [D76](#). The testing machine shall be equipped with a data-acquisition system.

6.4 *Clamps*—Side action clamps with rubber-coated flat jaw faces. The test specimen shall be held in such a way that slippage relative to the grips is prevented as much as possible. The width of the jaw faces should be equal to or larger than the sample width. If the clamps are of the air-actuated type, adjust the air pressure to prevent specimens slipping in the jaws, but keep the air pressure below the level that will cause specimens to break at the edge of the jaws. If the break is within 5 mm of the edge, the result must be discarded.

6.5 *Specimen Cutter*—a device capable of cutting specimens for testing that are uniform in width to within ± 0.2 mm of the specified specimen width and with edges parallel to within ± 0.1 mm. A double-blade strip cutter or a laser cutter is satisfactory for this requirement. Other cutting dies may also be used, provided they are found to comply with or exceed the tolerances within this standard. Single-blade paper cutters do not comply with the requirements for a specimen cutter for purposes of this test method.

7. Sampling, Test Specimens

7.1 For acceptance testing, sample each lot as directed in Test Methods [D202](#). Take the number of samples for testing specified for the specific property measurement to be made.

7.2 *Conditioning*—Bring all specimens to equilibrium in the atmosphere prior to sample cutting as directed in Practice [D1776](#) for Aramids.

7.3 *Preparation*—Cut the test specimens from each conditioned test unit of the sample. The two options for specimen size are:

Type 1: Length 205 mm $\pm$ 3 mm; width 15.0 mm $\pm$ 0.2 mm

Type 2: Length 205 mm $\pm$ 3 mm; width 25.4 mm $\pm$ 0.3 mm

7.4 *Number of Specimens*—At least five or preferably ten specimens per sample in machine, and at least five or preferably ten specimens per sample in the cross-machine direction.

8. Conditioning

8.1 Bring all specimens to equilibrium in the atmosphere prior to testing as directed in Practice [D1776](#) for Aramids.

9. Procedure

9.1 *Sample Preparation*—Cut the specimens according to Section 7.

9.2 *Conditioning*—Condition the samples as directed in [8.1](#).

9.3 *Measurement of Thickness*—Measure the thickness of the specimen according to Test Method [D374M](#).

9.4 *Measurement of Mass Per Unit Area*—Measure the grams per square meter by weighing the individual specimens as listed in [9.1](#).

9.5 *Gauge Length*—The gauge length shall have a total length for type 1 specimen size of 100 mm $\pm$ 1 mm and for type 2 of 127 mm $\pm$ 1 mm between the jaw faces.

9.6 *Crosshead Travel Rate*—The crosshead travel rate is 10 % of the nominal gauge length of the specimen. This rate of crosshead travel generally results in specimen rupture between 10 s and 30 s. In cases where rupture consistently requires greater than 30 s, a more rapid rate of crosshead travel must be used, so that specimen rupture occurs between 10 s and 30 s. Where a crosshead travel rate other than that stated above is used, the actual crosshead travel rate must be reported.

9.7 *Slack Start Procedure*—Clamp one end of the specimen between the jaws of one of the clamps and close it. Place the other end of the specimen through the jaws of the second clamp and keep the specimen just slack (zero tension) and close the clamp, taking care that the paper is positioned in the centerline