



Designation: D8021 – 23

Standard Guide for Blast Furnace and Steel Furnace Slag as Produced During the Manufacture of Iron and Steel¹

This standard is issued under the fixed designation D8021; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This standard is intended to provide guidance as to the appropriate/typical mineralogy observed when iron and steel slag, produced during the manufacture of iron and steel, is designated as a product. The included information covers the mineral properties of blast furnace slag and steel slag when they are manufactured in conjunction with the production of iron or steel, or both (**Note 1**).

NOTE 1—This guide is not intended to be used to determine the applicability of iron or steel slag, or both, for various applications. Terminology **D8** designates steel slag as a product, while Terminology **C125** designates blast furnace slag as a product. Its sole intent is to provide guidance as to the typical mineralogy when the iron or steel slag, or both, is designated as a product.

1.2 The values stated in SI units are to be regarded as standard. No other units are utilized in this standard.

1.3 The text of this standard references notes and footnotes that provide explanatory material. These notes and footnotes (excluding those in tables and figures) should not be considered as requirements of the specification.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This guide is under the jurisdiction of ASTM Committee **D04** on Road and Paving Materials and is the direct responsibility of Subcommittee **D04.99** on Sustainable Asphalt Pavement Materials and Construction.

Current edition approved Nov. 1, 2023. Published December 2023. Originally approved in 2020. Last previous edition approved in 2020 as D8021 – 20. DOI: 10.1520/D8021-23.

2. Referenced Documents

2.1 *ASTM Standards*:²

C125 Terminology Relating to Concrete and Concrete Aggregates

C595/C595M Specification for Blended Hydraulic Cements

C702/C702M Practice for Reducing Samples of Aggregate to Testing Size

C989/C989M Specification for Slag Cement for Use in Concrete and Mortars

C1252 Test Methods for Uncompacted Void Content of Fine Aggregate (as Influenced by Particle Shape, Surface Texture, and Grading)

D8 Terminology Relating to Materials for Roads and Pavements

D75/D75M Practice for Sampling Aggregates

3. Terminology

3.1 *Definitions*—For the definitions of terms used in this standard, refer to Terminology **D8**.

3.2 *Definitions of Terms Specific to This Standard*:

3.2.1 *blast furnace slag, n*—see Terminology **C125**.

3.2.1.1 *Discussion*—Slag, ferrous metal, blast furnace (granulated, GBS or air-cooled, ABFS or ABF)—Blast furnace slag is formed in a continuous process by the fusion of limestone (or dolomite, or a combination thereof) and other fluxes with the residues from the carbon source and the non-metallic components of the iron-bearing materials (for example, iron ore, iron sinter). Blast furnace slag is generated at temperatures above 1500 °C. Dependent on the manner of cooling of the liquid slag, it can be distinguished between crystalline, air-cooled blast furnace slag and glassy, granulated blast furnace slag. Various cooling processes are defined in Terminology **C125**.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.2.2 *slag, steelmaking, n*—steelmaking slags (SMS) are generated as products during the refining/modification of steel in the production process.

3.2.2.1 *Discussion*—Steelmaking slag is formed (for example, from the conversion of hot metal to steel) from the melting of scrap in an electric arc furnace or from the subsequent treatments of various refinements/modifications of the crude steel, or both. The composition of the slags varies depending on the process step in which they are produced. The molten slag which has tapping temperatures of around 1600 °C is discharged into pots or pits where it cools and solidifies to provide an artificial aggregate having a crystalline structure. They are sometimes referred to as ladle modification or caster slags.

3.2.3 *steel slag, BOF/converter, n*—a product of the conversion of liquid iron (hot metal) into steel during a batch process in a basic oxygen furnace.

3.2.3.1 *Discussion*—BOF/converter slag is generated by the addition of fluxes, such as limestone, dolomite, or both, during the blowing of oxygen into the melt. Due to the oxidizing conditions, some elements (like Fe and Mn) are partly oxidized and contribute to the formation of the slag. Furthermore, some components are either oxidized to gas (like carbon) or are chemically bound in the slag (like silicon or phosphorus). The liquid slag which has tapping temperatures of around 1600 °C is air cooled under controlled conditions in pits forming crystalline slag.

3.2.4 *steel slag, EAF C, n*—electric arc furnace slag generated during carbon steel production is a product of melting steel scrap in an electric arc furnace.

3.2.4.1 *Discussion*—Steel slag, EAF C (carbon steel production) is generated by the addition of fluxes, such as limestone, dolomite, or both. Furthermore, some elements of the melt are oxidized and contribute to the formation of the slag. The liquid slag which has tapping temperatures of around 1600 °C is typically air cooled (possibly applying small amounts of water) under controlled conditions in pots or pits forming crystalline slag.

3.2.5 *steel slag, EAF S, n*—electric arc furnace slag generated during stainless steel or high-alloy steel production.

3.2.5.1 *Discussion*—Steel slag, EAF S (stainless/high-alloy steel production) is generated by the addition of fluxes and reducing agents, for example lime or dolomite (or a combination thereof), silicon compounds, or aluminum. The liquid slag which has tapping temperatures of around 1600 °C is controlled and treated, if necessary, to improve the properties of the slag. Then, the slag is cooled under controlled conditions in pots or pits forming crystalline slag.

4. Significance and Use

4.1 This guide provides guidance as to the appropriate/typical mineralogy observed when iron and steel slag is produced during a variety of processes in the manufacture of iron and steel.

4.2 Slag can be considered a product based on the mineralogy of samples that are tested using X-ray diffraction, phase

recognition and characterization, powdered XRD-Rietveld analysis, and SEM-PARC results, using this guide.

5. Classification

5.1 Slag, ferrous metal, blast furnace (granulated, GBS or air-cooled, ABFS).

5.2 Slag, steelmaking, and converter—BOF.

5.3 Slag, steelmaking, and electric arc furnace—EAF C (carbon steel production).

5.4 Slag, steelmaking, electric arc furnace—EAF S (stainless/high-alloy steel production).

5.5 Slag, steelmaking—SMS.

6. Properties

6.1 Mineral Constituents:

6.1.1 Granulated blast furnace slag (GBS) typically contains up to 100 w/w% of glassy (vitreous) material (Specification C989/C989M). In some cases where a minor mineral component is detected, it is usually in the form of melilite (calcium-magnesium-silicate). Since the mineral component is usually minor, no characteristic mineral constituents can be given.

6.1.2 All other iron and steel slags exist predominantly in a crystalline form. Many are considered air cooled, although the process does allow for a water addition during cooling. The typical tables for ABFS, BOF, and EAF C include major primary mineral constituents which are characteristic for the fresh slag. The table for EAF S contains typical major mineral constituents (primary and secondary), and for SMS slags the most common mineral constituents are listed. Other mineral phases can occur, because the slags are UVCB³ substances. The XRD⁴ diagrams of all slags can show secondary mineral phases, for example hydroxides and carbonates, which are a result of weathering and aging of the slags. This is the case especially for EAF S slags and a large quantity of SMS slags, which are mostly soaked directly after the production.

6.1.3 Sometimes impurities, for example sand (quartz), can occur due to sampling, processing, or loading. In that case the quartz is not a fine-grained respirable crystalline silica, but granules, and therefore is considered to have no adverse health effects. The slag itself generally does not include crystalline quartz.

6.1.4 Slag, ferrous metal, blast furnace (granulated)—GBS, CAS⁵ No. 65996-69-2. Mineral constituents: glass (amorphous).

6.1.5 Slag, ferrous metal, blast furnace (air-cooled)—ABS, CAS No. 65996-69-2 (Table 1, Note 2).

NOTE 2—Air-cooled blast furnace slag from some steel plants may also contain a certain amount of glass.

6.1.6 Slag, steelmaking, converter—BOF, CAS No. 91722-09-7 (Table 2).

6.1.7 Slag, steelmaking, electric furnace (carbon steel production)—EAF C, CAS No. 91722-10-0 (Table 3).

³ UVCB: unknown or variable composition, complex reaction products, and biological materials.

⁴ XRD: X-ray powder diffraction.

⁵ CAS: Chemical Abstracts Service.