



Designation: D8088 – 16 (Reapproved 2022)

Standard Practice for Determination of the Six Major Rare Earth Elements in Fluid Catalytic Cracking Catalysts, Zeolites, Additives, and Related Materials by Inductively Coupled Plasma Optical Emission Spectroscopy¹

This standard is issued under the fixed designation D8088; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice describes the analysis of fluid catalytic cracking catalysts, rare earth exchanged zeolitic materials, additive and related materials when analyzed by ICP-OES for the six most common rare earth elements.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this Practice.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use. See Appendix X3.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

- C1109 Practice for Analysis of Aqueous Leachates from Nuclear Waste Materials Using Inductively Coupled Plasma-Atomic Emission Spectroscopy
- D1193 Specification for Reagent Water
- D3766 Terminology Relating to Catalysts and Catalysis
- D6299 Practice for Applying Statistical Quality Assurance and Control Charting Techniques to Evaluate Analytical

Measurement System Performance

- D6349 Test Method for Determination of Major and Minor Elements in Coal, Coke, and Solid Residues from Combustion of Coal and Coke by Inductively Coupled Plasma—Atomic Emission Spectrometry
 - D7085 Guide for Determination of Chemical Elements in Fluid Catalytic Cracking Catalysts by X-ray Fluorescence Spectrometry (XRF)
 - D7260 Practice for Optimization, Calibration, and Validation of Inductively Coupled Plasma-Atomic Emission Spectrometry (ICP-AES) for Elemental Analysis of Petroleum Products and Lubricants
 - D7442 Practice for Sample Preparation of Fluid Catalytic Cracking Catalysts and Zeolites for Elemental Analysis by Inductively Coupled Plasma Optical Emission Spectroscopy
 - E1479 Practice for Describing and Specifying Inductively Coupled Plasma Atomic Emission Spectrometers
- 2.2 *EPA Standard:*³
- Method 6010B Inductively Coupled Plasma-Atomic Emission Spectrometry

3. Terminology

- 3.1 *Definitions*—See Terminology D3766.
- 3.2 *Definitions of Terms Specific to This Standard:*
 - 3.2.1 *ICP-OES*—Inductively Coupled Plasma Optical Emission Spectroscopy
 - 3.2.2 *FCC*—Fluid Catalytic Cracking
 - 3.2.3 *Water*—Defined as ASTM Type I or highest quality available as defined in Specification D1193.

4. Summary of Practice

4.1 Specimens are prepared using one of the three preparation techniques described in Practice D7442-08a. The result should be a clear, dilute acidic solution suitable for ICP-OES.

¹ This practice is under the jurisdiction of ASTM Committee D32 on Catalysts and is the direct responsibility of Subcommittee D32.03 on Chemical Composition. Current edition approved April 1, 2022. Published May 2022. Originally approved in 2016. Last previous edition approved in 2016 as D8088 – 16. DOI: 10.1520/D8088-16R22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from United States Environmental Protection Agency (EPA), William Jefferson Clinton Bldg., 1200 Pennsylvania Ave., NW, Washington, DC 20460, <http://www.epa.gov>.

The final concentration should be 1.0 g of the test specimen prepared and diluted into a 250 mL volumetric flask. The test solutions are introduced into the plasma torch of the ICP instrument where excitation occurs. Characteristic atomic line emission spectra are produced by a radio-frequency inductively coupled plasma. The spectra are dispersed by a high resolution grating and the intensities of the individual lines are measured. By comparing emission intensities of the elemental lines in the test specimens with emission intensities measured in the standards, the concentration of the elements in the test specimen can be calculated. The internal standard will compensate for variations in test specimen introduction efficiency.

4.2 Details of the instrument components are given in Practice [E1479](#). This Practice provides a good summary of instrument calibration and verification techniques.

4.3 Practice [D7260](#), although primarily for non-aqueous applications, provides a good description of the basic components that make up an ICP-OES instrument.

4.4 This practice describes the analysis of the six major rare earth elements found in catalyst and related materials. It can easily be extended to any additional elements by following the protocols outlined in this Practice. Guide [D7085](#) provides a list of the elements above 10 ppm commonly found in equilibrium fluid catalytic cracking catalysts. EPA Method 6010B is a good primer for those not familiar with the technique. It describes the analysis of water and waste water for numerous elements at low concentration.

5. Significance and Use

5.1 The chemical composition of catalysts and catalyst materials is an important indicator of catalyst performance and is a valuable tool for assessing parameters in a FCCU process. This practice will be useful to catalyst manufacturers and petroleum refiners for quality verification and performance evaluation, and to environmental authorities at the state and federal levels for evaluation and verification of various compliance programs ([1](#), [2](#), [3](#)).

6. Reagents

6.1 All reagents should conform to American Chemical Society (ACS) specifications. Ultra-high purity standards and reference materials are commercially available from recognized vendors.

6.2 *Perchloric Acid*, concentrated, 69 to 72 %.

6.3 *Hydrofluoric Acid*, concentrated, 48 % (Refer to the Safety Information in [Appendix X3](#)).

6.4 *Sulfuric Acid*, H_2SO_4 , concentrated, 94 %.

6.5 *Nitric Acid*, HNO_3 , concentrated, 65 %.

6.6 *Hydrochloric Acid*, 1:1 HCl (concentrated HCl, 38, Diluted 1:1).

6.7 *Hydrogen Peroxide*, 3 %.

6.8 *Lithium Borate Fluxes*, lithium tetra-borate or meta-borate, or both.

6.9 *Boric Acid Solution*, 3 %.

6.10 *Water*, Type I preferred, or highest quality available.

7. Preparation of Calibration Standards

7.1 Determine the method that will be used for the preparation of the test specimens. Determine the element that will be used as an internal standard. The sample test specimens should contain no appreciable amount of the element selected as an internal standard. Common elements used as internal standards for catalysts and related materials are cobalt and scandium.

7.2 For the purpose of this discussion, we will assume a perchloric acid digestion with cobalt as the internal standard.

7.3 Prepare ten 250 mL volumetric flasks. Number each flask. Fill each flask half full with water and then into each flask add 20 mL of perchloric acid, 15 mL of 3 % boric acid solution, and 10 mL of hydrochloric acid.

7.4 Label flask number 1 “Reagent Blank.” Add 1 mL of internal standard. For this example, 1 mL of a 10 000 ppm solution of cobalt and dilute to volume with water.

7.5 Into flask number 2, add 25 mL of 10 000 ppm aluminum. Label flask number 2 “Sample Blank.” Add 1 mL of the internal standard solution and dilute to volume with water.

7.6 Into flask number 3, add 10 mL of a 1000 ppm lanthanum solution. Add 1 mL of internal standard solution and dilute to volume with water. Label “La Std.”

7.7 Into flask number 4, add 10 mL of a 1000 ppm cerium solution. Add 1 mL of internal standard solution and dilute to volume with water. Label “Ce Std.”

7.8 Into flask number 5, add 5 mL of a 1000 ppm neodymium solution. Add 1 mL of internal standard solution and dilute to volume with water. Label “Nd Std.”

7.9 Into flask number 6, add 5 mL of a 1000 ppm praseodymium solution. Add 1 mL of internal standard solution and dilute to volume with water. Label “Pr Std.”

7.10 Into flask number 7, add 5 mL of a 1000 ppm gadolinium solution. Add 1 mL of internal standard solution and dilute to volume with water. Label “Gd Std.”

7.11 Into flask number 8, add 2 mL of a 1000 ppm solution of samarium. Add 1 mL of internal standard solution and dilute to volume with water. Label “Sm Std.”

7.12 Into flask number 9, add:
25 mL of 10 000 ppm aluminum solution,
10 mL of 1000 ppm lanthanum solution,
5 mL of 1000 ppm cerium solution,
2 mL of 1000 ppm neodymium solution,
5 mL of 1000 ppm praseodymium solution,
3 mL of 1000 ppm gadolinium solution, and
2 mL of 1000 ppm samarium solution.

7.12.1 Add 1 mL of internal standard solution and dilute to volume with water. Label “Check Std #1.”

7.13 Into flask number 10, add:
25 mL of 10 000 ppm aluminum solution,
5 mL of 1000 ppm lanthanum solution,
10 mL of 1000 ppm cerium solution,
5 mL of 1000 ppm neodymium solution,