



Designation: D8200 – 22

Standard Practice for Creating a Correlation to Compare Particle Size Distribution Results of Proppants by Dynamic Imaging Analyzers and Sieves¹

This standard is issued under the fixed designation D8200; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice describes procedural steps to create a correlation that can be used to compare results of proppant size distributions between dynamic imaging analyzers (analyzers) and prescribed sieve sets.

1.2 The proppant size and distribution specifications that are included in this practice are listed in API Standard 19C (API 19C) and shown in [Table 1](#), however as industry evolves additional specifications may come into use and this practice can be used with those as well.

1.3 This practice may not be applicable to all proppant types and designations. The acceptability of the correlations determined are judged by the operator.

1.4 The values stated in SI units are to be regarded as the standard, except sieve designations are typically identified using the ‘alternative’ system in accordance with Practice [E11](#), such as 3 in. and No. 200 instead of the ‘standard’ system of 75 mm and 75 μm, respectively.

1.5 Observed and calculated values shall conform to the guidelines for significant digits and rounding established in Practice [D6026](#), unless superseded by this standard.

1.5.1 The procedures used to specify how data are collected/recorded and calculated in Practice [D6026](#) are regarded as the industry standard. In addition, they are representative of the significant digits that generally should be retained. The procedures used do not consider material variation, purpose for obtaining the data, special purpose studies, or any considerations for the user’s objectives; and it is common practice to increase or reduce significant digits of reported data to be commensurate with these considerations. It is beyond the scope of these test methods to consider significant digits used in analysis methods for engineering data.

1.6 *This practice offers a set of instructions for performing one or more specific operations. This document cannot replace*

education or experience and should be used in conjunction with professional judgment. Not all aspects of this practice may be applicable in all circumstances. This ASTM standard is not intended to represent or replace the standard of care by which the adequacy of a given professional service must be judged, nor should this document be applied without consideration of a project’s many unique aspects. The word “Standard” in the title means only that the document has been approved through the ASTM consensus process.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.8 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D75 Practice for Sampling Aggregates](#)

[D653 Terminology Relating to Soil, Rock, and Contained Fluids](#)

[D3740 Practice for Minimum Requirements for Agencies Engaged in Testing and/or Inspection of Soil and Rock as Used in Engineering Design and Construction](#)

[D4753 Guide for Evaluating, Selecting, and Specifying Balances and Standard Masses for Use in Soil, Rock, and Construction Materials Testing](#)

[D6026 Practice for Using Significant Digits and Data Records in Geotechnical Data](#)

[D6913 Test Methods for Particle-Size Distribution \(Gradation\) of Soils Using Sieve Analysis](#)

¹ This practice is under the jurisdiction of ASTM Committee [D18](#) on Soil and Rock and is the direct responsibility of Subcommittee [D18.26](#) on Hydraulic Fracturing.

Current edition approved Nov. 1, 2022. Published November 2022. DOI: 10.1520/D8200-22

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

2.2 API Standard:³

Standard 19C Measurement of and Specifications for Proppants Used in Hydraulic Fracturing and Gravel Packing Operations.

3. Terminology

3.1 For definitions of common technical terms used in this standard refer to Terminology **D653**.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *correlation fit file, n—in proppant particle size testing*, a software based, data analysis algorithm used to correlate analyzer results to sieve results.

3.2.2 *dynamic imaging analyzer, n—in proppant particle size testing*, any instrument employing a camera or other visual sensor, with appropriate illumination, to digitally capture and analyze images, via an image processor, of moving particles conducted through a measurement zone.

3.2.3 *proppant, n—in hydraulic fracturing*, a solid granular material designed to keep an induced hydraulic fracture open during or following a fracturing treatment.

3.2.3.1 *Discussion*—Typically such granular material is composed of processed sand, resin coated sand, ceramic, resin coated ceramic and other manufactured materials having a limited range of particle/sieve sizes which are less than 4.75 mm and with negligible fines.

3.2.4 *reticle, n—a measurement scale*, traceable to NIST, with 100 μm and 10 μm subdivisions which spans approximately 80 % of the field of view which is used in order to calibrate the analyzer.

4. Summary of Practice

4.1 The practice contains procedural steps that can be followed in order to correlate results of proppant size distributions determined from prescribed sieve sets (see **Table 1**) and results from analyzers.

4.2 A correlation is determined based on testing of the actual proppant it is being created for. Representative proppant samples are obtained and test specimens are created and tested by the sieve sets and then by the analyzer. The data is compared and a correlation is determined and then tested on additional proppant specimens.

4.3 Each correlation fit file is created for each proppant designation and contains the correlation factors the analyzer uses to match its results to the sieve set. Each is particular to a single set of test sieves. If physical changes are made to either

the sieve set or analyzer the procedure must be repeated to re-establish the correlation.

5. Significance and Use

5.1 The ability to correlate results of analyzers to sieve sets enables the use of non-sieve methods to be employed that give comparable results to each other.

5.2 The use of analyzers for proppant measurement has the benefit of providing particle shape characteristics which are important in the performance of these materials. Shape analysis is currently done by operator's determination based on a visual observation of a small number of particles per API 19C. Available information from imaging analysis of many particles can be used to assess the proppant shape characteristics as opposed to just a small number.

6. Apparatus

6.1 *Dynamic Imaging Analyzer*.

6.2 *Calibration Sieves*, specified in **Table 1**, 8 in. diameter in size meeting calibration grade per Specification **E11**.

6.3 *Working Sieves*, specified in **Table 1**, 8 in. diameter in size meeting compliance grade per Specification **E11**.

6.4 *Box Sampling Device*, meeting requirements of Test Method **D6913**.

6.5 *Sample Splitter*, meeting requirements of Test Method **D6913**.

6.6 *No. 200 wash screen*.

6.7 *Balance*, minimum 500 g capacity and meeting Guide **D4753** with a minimum resolution of 0.01 g.

6.8 *Oven*, capable of containing a 500 g proppant sample and maintaining a uniform temperature of $110\text{ }^{\circ}\text{C} \pm 5\text{ }^{\circ}\text{C}$.

7. Reagents and Materials

7.1 *Proppant*, sampled from the actual materials that will be measured going forward.

8. Sample and Specimen Preparation

8.1 A total of three representative proppant samples, each approximately 200 g in mass, will be obtained in accordance with Practice **D75**.

8.2 Follow the moist procedure, single sieve set sieving instructions of Test Method **D6913** for the following:

8.2.1 Use a sample splitter (**6.5**) to divide each sample into two specimens of approximately 100 g that will be used to create the correlation.

8.2.2 Dry each specimen and determine its mass.

8.2.3 Wash each specimen using a No. 200 wash screen, then dry the sample and record its mass. The difference in mass from **8.2.2** represents the amount passing No. 200.

³ Available from American Petroleum Institute (API), 200 Massachusetts Ave. NW, Suite 1100, Washington, DC 20001, <http://www.api.org>.