



Designation: D8391 – 22^{ε1}

Standard Specification for Demonstrating Equivalent Fire Performance for Wood- Based Floor Framing Members to Unprotected 2 by 10 Dimension Lumber or Equal-Sized Structural Composite Lumber¹

This standard is issued under the fixed designation D8391; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Information about copyrighted text was included in March 2023.

1. Scope

1.1 This specification provides the test methodology and procedures to demonstrate that the fire performance of wood-based floor framing members is equivalent to unprotected 2 by 10 dimension lumber or equal-sized structural composite lumber (SCL) floor joists used in interior floor assemblies. This specification is applicable to floor framing members with or without applied treatments or materials used to increase fire resistance, including fire-resistive paints, coatings, or chemical treatments, and including mechanically attached or adhered fire protection materials. It is applicable to any wood-based residential floor framing member product including, but not limited to, prefabricated wood I-joists, open-web wood joists, and trusses with wood flanges and wood or metal web members. In addition, specific requirements for the evaluation of fire-resistive paints, coatings, or chemical treatments used with these floor framing members are included.

NOTE 1—This specification provides a method of comparing the fire performance of floor framing members to benchmarked performance of unprotected 2 by 10 dimension lumber or equal-sized SCL floor joists. It has been successfully used to evaluate the performance of prefabricated wood I-joists and wood trusses with various forms of fire protection. While the principles of this specification are generally applicable to all floor framing members, the development of the specification did not consider additional requirements or modifications which may be necessary for the evaluation of floor framing members of other materials, such as steel joists or trusses.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appro-*

priate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

- D9 Terminology Relating to Wood and Wood-Based Products
- D198 Test Methods of Static Tests of Lumber in Structural Sizes
- D610 Practice for Evaluating Degree of Rusting on Painted Steel Surfaces
- D1037 Test Methods for Evaluating Properties of Wood-Base Fiber and Particle Panel Materials
- D1761 Test Methods for Mechanical Fasteners in Wood and Wood-Based Materials
- D2898 Practice for Accelerated Weathering of Fire-Retardant-Treated Wood for Fire Testing
- D2915 Practice for Sampling and Data-Analysis for Structural Wood and Wood-Based Products
- D4761 Test Methods for Mechanical Properties of Lumber and Wood-Based Structural Materials
- D5055 Specification for Establishing and Monitoring Structural Capacities of Prefabricated Wood I-Joists
- D5664 Test Method for Evaluating the Effects of Fire-Retardant Treatments and Elevated Temperatures on Strength Properties of Fire-Retardant Treated Lumber
- D7032 Specification for Establishing Performance Ratings

¹ This specification is under the jurisdiction of ASTM Committee D07 on Wood and is the direct responsibility of Subcommittee D07.05 on Wood Assemblies.

Current edition approved Jan. 1, 2022. Published January 2022. DOI: 10.1520/D8391-22E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

for Wood-Plastic Composite and Plastic Lumber Deck Boards, Stair Treads, Guards, and Handrails

E119 Test Methods for Fire Tests of Building Construction and Materials

E176 Terminology of Fire Standards

E2309 Practices for Verification of Displacement Measuring Systems and Devices Used in Material Testing Machines

E3048 Test Method for Determination of Time to Burn-Through Using the Intermediate Scale Calorimeter (ICAL) Radiant Panel

2.2 *TPI Standard*.³

ANSI/TPI 1 National Design Standard for Metal Plate Connected Wood Truss Construction

2.3 *AWC Standard*.⁴

ANSI/AWC NDS National Design Specification for Wood Construction

2.4 *AWPA Standard*.⁵

AWPA E12 Standard Method of Determining Corrosion of Metal in Contact with Treated Wood

2.5 *ISO Standards*.⁶

ISO/IEC 17011 Conformity Assessment – Requirements for Accreditation Bodies Accrediting Conformity Assessment Bodies

ISO/IEC 17020 Conformity Assessment – Requirements for the Operation of Various Types of Bodies Performing Inspection

ISO/IEC 17065 Conformity Assessment – Requirements for Bodies Certifying Products Processes and Services

2.6 *U.S. Department of Commerce Standards*.⁷

PS 1 Structural Plywood, U.S. Department of Commerce Voluntary Product Standard

PS 2 Performance Standard for Wood Structural Panels, U.S. Department of Commerce Voluntary Product Standard⁷

3. Terminology

3.1 *Definitions*—Definitions used in this specification are in accordance with Terminology **D9** and Terminology **E176**, unless otherwise indicated.

3.2 *Definitions of Terms Specific to This Standard*:

3.2.1 *chemical treatment, n*—chemical substance applied to the structural member with the purpose of improving performance in fire.

3.2.2 *factory-applied, adj*—applied in a factory setting by or under the direction of the manufacturer of the floor framing members.

3.2.3 *field-applied, adj*—installed after the time of manufacture of the floor framing member by an entity not under the direction of the manufacturer of the floor framing member.

3.2.4 *floor joist, n*—structural floor framing member.

3.2.5 *prefabricated wood I-joist, n*—structural framing member manufactured using sawn or structural composite lumber flanges and structural panel webs, bonded together with exterior exposure adhesives, forming an “I” cross-sectional shape and primarily used as a joist in floor and roof construction.

4. Applicability

4.1 All floor framing members to be evaluated in accordance with this specification, regardless of protection method, shall be subject to the requirements in Sections 5 through 9.

4.2 Floor framing members relying on protection from fire-resistive paints, coatings, and chemical treatments shall meet additional requirements described in **Annex A1**. Provisions are included in this specification for both factory-applied products and field-applied products.

5. Test Performance Requirements

5.1 The floor framing members being evaluated shall support not less than 50 % of the load associated with the allowable stress design (ASD) reference design value in bending for an elapsed time of not less than 15 min, 30 s from the beginning of the furnace test to the end of the test, while meeting the specified deflection criteria.⁸

NOTE 2—The required minimum duration for the test was derived using the methodology specified in Chapter 16 of the NDS assuming unprotected 2 by 10 dimension lumber or equal-sized structural composite lumber floor joists, a three-sided fire exposure, a nominal char rate of 1.5 in./h (38.1 mm/h), a bending strength to ASD ratio of 2.85, and a load corresponding to 50 % of the full ASD bending design load. It is recognized that achieving the required test duration of 15 min, 30 s with a load greater than 50 % of the full ASD bending design load would be conservative relative to the reference case, therefore no upper limit on loading is imposed.⁸

5.2 The end of the test shall be defined by the first occurrence of one of the following:⁸

5.2.1 The furnace is extinguished for any reason, or

5.2.2 Any individual framing member within the test assembly ruptures, or

5.2.3 The test assembly center span deflection, as determined in accordance with **8.2**, exceeds 1/40 of the clear span, or

5.2.4 The deflection rate, dx/dt , decreases without recovering,

where:

dt = a 1-s time interval, and

dx = deflection increment in a 1-s time interval, dt , after smoothing of deflection data using a centered moving average with a time window of 10 s.

⁸ Acceptance Criteria for Prefabricated Wood I-Joists (AC14), Copyright © 2019 ICC-ES. All rights reserved.

³ Available from Truss Plate Institute, 218 N. Lee Street, Ste 312, Alexandria, VA 22134.

⁴ Available from American Wood Council (AWC), 222 Catocin Circle SE, Suite 201, Leesburg, VA 20175, <https://www.awc.org>.

⁵ Available from American Wood Protection Association (AWPA), P.O. Box 361784, Birmingham, AL 35236-1784, <http://www.awpa.com>.

⁶ Available from International Organization for Standardization (ISO), ISO Central Secretariat, Chemin de Blandonnet 8, CP 401, 1214 Vernier, Geneva, Switzerland, <https://www.iso.org>.

⁷ Available from U.S. Government Publishing Office (GPO), 732 N. Capitol St., NW, Washington, DC 20401, <http://www.gpo.gov>.