



Designation: E1095 – 99 (Reapproved 2022)

Standard Specification for Common Laboratory Glass Funnels¹

This standard is issued under the fixed designation E1095; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers common laboratory or filter funnels, and filling or powder funnels for general laboratory use.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- E438 Specification for Glasses in Laboratory Apparatus
- E671 Specification for Maximum Permissible Thermal Residual Stress in Annealed Glass Laboratory Apparatus
- E920 Specification for Commercially Packaged Laboratory Apparatus
- E921 Specification for Export Packaged Laboratory Apparatus
- E1133 Practice for Performance Testing of Packaged Laboratory Apparatus for United States Government Procurements
- E1157 Specification for Sampling and Testing of Reusable Laboratory Glassware

3. Classification

3.1 There shall be four types of laboratory glass funnels further divided into classes.

3.1.1 *Type 1*—Common laboratory funnel with smooth inner surface, divided into the following three classes:

¹ This specification is under the jurisdiction of ASTM Committee E41 on Laboratory Apparatus and is the direct responsibility of Subcommittee E41.01 on Laboratory Ware and Supplies.

Current edition approved Jan. 1, 2022. Published February 2022. Originally approved in 1986. Last previous edition approved in 2016 as E1095 – 99(2016). DOI: 10.1520/E1095-99R22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.1.1 *Class A, (short stem)*—Sizes 25, 35, 45, 55, 65, 75, 90, 100, 125, and 150-mm diameters.

3.1.1.2 *Class B, (long stem)*—Sizes 35, 45, 50, 55, 65, 75, 90, 100, 125, 150, 200, 250, and 300-mm diameters.

3.1.1.3 *Class C, (without stem)*—Sizes 50, 75, and 100-mm diameters.

3.1.2 *Type 2*—Laboratory funnel with fluted inner wall. The flutes are small grooves or depressions running upward from the bottom zone of the bowl.

3.1.2.1 *Class A, (short stem)*—Sizes 50, 65, 75, and 100-mm diameters.

3.1.2.2 *Class B, (long stem)*—Sizes 50, 65, 75, and 100-mm diameters.

3.1.3 *Type 3*—Laboratory funnel with ribbed inner wall. The ribs are small raised protuberances running from funnel rim toward the stem.

3.1.3.1 *Class A, (short stem)*—Sizes 50, 65, 75, and 100-mm diameters.

3.1.3.2 *Class B, (long stem)*—Sizes 50, 65, 75, and 100-mm diameters.

3.1.4 *Type 4*—Filling or powder funnels.

3.1.4.1 *Short, Wide Diameter Stem*—Sizes 60, 65, 75, 80, 100, 125, and 150-mm diameters.

4. Material and Annealing

4.1 *Material*—Funnels shall be made of glass conforming to the requirement of Type 1, Class A or B or Type 2 of Specification E438.

4.2 *Annealing*—Maximum residual stress shall be such as to conform to Specification E671.

5. Design

5.1 *Bowl*—The inner wall of the bowl shall diverge from the stem at an angle of $30 \pm 1.2^\circ$. The bowl shall be securely sealed to the stem. The axis of the funnel bowl shall coincide with the stem axis and the rim shall be perpendicular to this axis. The edge of the rim shall be mold finish, beaded or ground to a horizontal surface, as specified.

5.1.1 *Type 1*—Bowl of common funnels shall be plain.

5.1.2 *Type 1, Class C*—Bottom of bowl shall be ground flat.

5.1.3 *Type 2*—Bowl of fluted funnels shall have an inner wall with 8 equally spaced small grooves or depressions that shall extend upward from the inner bottom zone of the bowl $\frac{1}{2}$ to $\frac{5}{8}$ times the inner bowl depth.