



Designation: E255 – 23

Standard Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition¹

This standard is issued under the fixed designation E255; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice describes the sampling of copper (except electrolytic cathode) and copper alloys in either cast or wrought form for the determination of composition.

1.2 Cast products may be in the form of cake, billet, wire bar, ingot, ingot bar, or casting.

1.3 Wrought products may be in the form of flat, pipe, tube, rod, bar, shape, or forging.

1.4 This practice is not intended to supersede or replace existing specification requirements for the sampling of a particular material.

1.5 The values stated in SI units are to be regarded as standard. The values in parentheses are given for information only.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use. A specific precautionary statement appears in Appendix X4.*

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

¹ This practice is under the jurisdiction of ASTM Committee E01 on Analytical Chemistry for Metals, Ores, and Related Materials and is the direct responsibility of Subcommittee E01.05 on Cu, Pb, Zn, Cd, Sn, Be, Precious Metals, their Alloys, and Related Metals.

Current edition approved June 1, 2023. Published June 2023. Originally approved in 1966. Last previous edition approved in 2014 as E255 – 07 (2014) which was withdrawn January 2023 and reinstated in June 2023. DOI: 10.1520/E0255-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E135 Terminology Relating to Analytical Chemistry for Metals, Ores, and Related Materials

3. Terminology

3.1 For definitions of terms used in this practice, refer to Terminology E135.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *lot, n*—as used in this practice, the unit to be sampled, in pounds or pieces.

3.2.2 *test sample, n*—as used in this practice, a composite of material taken by approximate proportional weight from each of the test pieces and from which the test portion shall be taken.

NOTE 1—Appendix X1 describes the refinery shapes. Appendix X2 describes the fabricators' forms.

4. Significance and Use

4.1 This practice is intended primarily for the sampling of copper and copper alloys for compliance with compositional specification requirements.

4.2 The selection of correct test pieces and the preparation of a representative sample from such test pieces are necessary prerequisites to every analysis. The analytical results will be of little value unless the sample represents the average composition of the material from which it was prepared.

5. Selection of Test Pieces

5.1 Casting:

5.1.1 Finished Product or Shipment Sample:

5.1.1.1 A shipping lot shall consist of all castings of the same configuration and size necessary to comply with the requirements of a single purchase order.

5.1.1.2 Castings are frequently produced in advance of orders and manufacturer's or foundry lots may intermingle in stock.

5.1.1.3 Since the size and configuration of castings vary, the number of test pieces to be selected shall be subject to agreement between the manufacturer or supplier and the purchaser.

5.1.2 Manufacturer's or Foundry Sample:

5.1.2.1 For routine sampling and at the option of the manufacturer, a lot shall consist of the following:

(a) All of the metal poured from a single furnace or crucible melt, or

(b) All of the metal poured from two or more furnaces into a single ladle, or

(c) All of the metal poured from a continuous melting furnace between charges, or

(d) All of the metal poured from an individual melting furnace, or group of melting furnaces, having a uniform melting stock, operating during the course of one-half shift, not to exceed 5 h.

5.1.2.2 The sample taken for lot analysis shall be obtained during the pouring of the liquid metal into the mold, or molds, in such a manner as to be representative of the lot and able to be drilled or used in solid form.

5.1.2.3 Plant sampling practices should be developed and implemented which will give homogeneous samples representative of the cast or heat, and free of porosity. Analytical results are frequently obtained by an atomic emission technique and, depending upon the metallurgical history of the sample, results may vary. Therefore, it is advisable to cool or quench the sample in a reproducible manner.

5.1.2.4 When foundry lot traceability is specified in the purchase order, additional samples shall be taken, identified, and set aside when so requested by the purchaser.

5.2 Cast Product:

5.2.1 For routine sampling and at the option of the manufacturer, a lot shall consist of all of the metal poured from a single furnace melt or all of the metal poured from a continuous melting furnace during a single casting cycle.

5.2.2 Unless otherwise agreed between the manufacturer and the purchaser, sampling of a single lot shall be as follows:

5.2.2.1 *Single Furnace Charge*—The number of samples required depends on the size of the melting furnace and homogeneity of the melt. A small well-stirred, alloying furnace such as one inductively heated and of less than 22 680 kg (50 000 lb) shall require but one sample taken midway in the pour. A large mechanically stirred furnace shall require a minimum of three samples taken, one each at the beginning, middle, and end of the casting period.

5.2.2.2 *Continuous Melting Furnace*—A minimum of one sample shall be taken for each 3 h of the casting cycle.

5.3 Wrought Products:

5.3.1 Finished Product or Shipment Sample:

5.3.1.1 The lot size, gross sample size, and selection of test pieces shall be as follows:

(a) *Lot Size*—An inspection lot shall be 4535.9 kg (10 000 lb) or less of the same mill form, alloy, temper, and nominal dimensions, subject to inspection at one time; or it shall be the product of one cast bar from a single melt charge, whose weight shall not exceed 9071.9 kg (20 000 lb), which was continuously processed and subject to inspection at one time.

(b) *Gross Sample*—The gross sample shall be four or more pieces selected to be representative of the lot. Should the lot consist of four pieces or less, the entire lot shall constitute the gross sample.

(c) *Test Piece*—Each test piece shall be selected to be representative of the lot.

5.3.1.2 When possible, test pieces shall be selected in a manner that will represent correctly the material furnished but also avoid needless destruction of finished product (such as when samples representative of the material are available from other sources).

5.3.2 Manufacturer's or Foundry Sample:

5.3.2.1 For routine sampling, the manufacturer shall have the option of taking samples during the course of manufacture. Samples may be taken at the time castings are poured or from the semifinished product.

5.3.2.2 When samples are taken at the time castings are poured, at least one sample shall be taken for each group of castings poured from the source of molten metal.

5.3.2.3 When samples are taken from the semifinished product, a sample shall be taken to represent each 4535.9 kg (10 000 lb), or fraction thereof, except that not more than one sample shall be required per piece. Only one sample need be taken from the semifinished product of one cast bar from a single melt charge continuously processed.

6. Sampling

6.1 General Considerations:

6.1.1 The saw, drill bit, cutter, or other tool used shall be thoroughly cleaned prior to use. The speed of sampling shall be so regulated that excessive heating and consequent oxidation is avoided. Carbide-tipped tools are recommended. Steel tools, when used, shall be magnetizable to assist in the removal of extraneous iron. Only carbide-tipped or other wear-resistant tools shall be used to sample metal which contains a magnetic phase.

6.1.1.1 In the rare instance where tool lubricant is necessary to obtain a satisfactory sample, the lubricant shall be one that will not react with the metal. The lubricant shall be completely removed immediately after the sampling operation by washing with a solvent which also does not react with the metal.

6.1.2 The test pieces shall be clean and free from scale, dirt, oil, grease, and other extraneous contaminants before sampling.

6.1.3 Test pieces taken from product not subject to significant segregation shall be sampled by drilling, milling, or sawing each test piece. Sampling may also be performed by clipping if pieces are thin or small.

6.1.4 Test pieces taken from product subject to significant segregation shall be sampled by drilling or sawing completely through each test piece, or by milling the entire cross section of each test piece.

6.2 Finished Product or Shipment Sampling:

6.2.1 Castings:

6.2.1.1 Different parts of a casting may vary in composition. Therefore, a sample from a single casting shall be taken with care to be representative of that casting. To obtain a sample representative of the finished product lot, a number of test pieces should be sampled individually. Regardless, the sample should be taken that will be representative and large enough to suffice for all of the required determinations.

6.2.1.2 Where possible, depending on size and configuration, the casting shall be sampled by drilling five holes equally spaced around or along the casting. The drilling