



Designation: E95 – 68 (Reapproved 2022)

Standard Specification for Cell-Type Oven with Controlled Rates of Ventilation¹

This standard is issued under the fixed designation E95; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the general requirements of a cell-type oven with controlled rates of ventilation for determining loss in weight or changes in properties of materials on heating at elevated temperatures. These specifications take into account the fact that chamber geometry, rate of ventilation, and temperature each affect the rate of loss of volatile constituents from a material, or the rate of change in other properties. This oven is recommended whenever the results are dependent on the time and temperature of heating, the amount of ventilation, or both. It is assumed that specific requirements such as specimen shape and dimensions, rate of ventilation, time, and temperature will be included in the applicable material specifications or test methods.

NOTE 1—Ovens meeting these specifications have been found useful for determination of plasticizer loss in plastics, and for controlled aging of elastomers and plastics.

1.2 The values stated in inch-pound units are to be regarded as the standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D1870 Practice for Elevated Temperature Aging Using a Tubular Oven (Withdrawn 1998)³

¹ This specification is under the jurisdiction of ASTM Committee E41 on Laboratory Apparatus and is the direct responsibility of Subcommittee E41.06 on Laboratory Instruments and Equipment.

Current edition approved Jan. 1, 2022. Published February 2022. Originally approved in 1952. Last previous edition approved in 2016 as E95 – 68(2016). DOI: 10.1520/E0095-68R22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

3. Types

3.1 Ovens are classified according to ventilation rate within the cells, provision being made for low (LV) and high (HV) ventilation rates. Thus, for materials showing low rates of weight loss a means is provided for their evaluation without the necessity of providing the excessive heat input required by the higher ventilation rate. It should, however, be established by experiment when using the LV-type oven that the rate of ventilation is adequate to avoid stagnation at the surface of the specimens, as would be caused, for example, by high rates of diffusion of volatile constituents through the body of the specimen.

3.2 Oven types are classified as follows:

Type	Ventilation Rate, m/min
LV	0.25 to 25
HV	100 to 250

4. Requirements

4.1 The oven shall consist of one or more cylindrical cells, each having a minimum diameter of 35 mm (1.4 in.) and a minimum length of 300 mm (12 in.). The cells shall be mounted in a thermostatically controlled, heat-transfer medium: for example, an aluminum block, a liquid bath, or a circulating-air oven. The cells shall not be constructed of copper or a copper alloy.

4.2 The design of the oven shall be such that heated air enters one end of the cell and is exhausted from the other end of it without being recirculated. In order to prevent cross-migration of volatile constituents contained in the specimens being tested, air passing over a specimen in one cell shall not come in contact with specimens in other cells.

4.3 Air entering the cells shall have been filtered and preheated to within 1 °C of the specified temperature for the space occupied by the specimen. The design shall also permit the cells to be cleaned easily after each test.

4.4 Provision shall be made for metering the airflow through each cell within $\pm 10\%$ of any desired rate within the range of the particular type of oven. The air may be metered to each tube, or a single pressure-control device leading to a plenum chamber may be used. If a plenum chamber is used, cells should be connected to it by passageways or orifices having restrictions to assure the same rate of airflow to each cell. The rate of flow may be measured on the entering air at room