



Standard Guide for Steel Hull Construction Tolerances [Metric]¹

This standard is issued under the fixed designation F 1053/F1053M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide outlines permissible deviations and distortions in new construction of steel hulls, in accordance with good fit criteria and strength requirements.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Terminology

2.1 Definitions:

2.1.1 *standard range*—level of construction accuracy that is normally expected to be achieved using conventional ship-building practice.

2.1.2 *tolerance limits*—construction tolerance range within which no corrective action need be taken.

3. Application

3.1 Table 1, appearing as Fig. 1, Fig. 2, Fig. 3, Fig. 4, and

Fig. 5, is to be used as a guide in determining permissible deviations, distortions, unfairness, and construction inaccuracies in principal strength members in new construction of steel hulls. The principal strength members include longitudinal strength members within the 0.4 length amidships, as well as other structurally critical hull members. This guide is intended for use with ordinary strength steels.

4. Corrective Action

4.1 Construction inaccuracies falling outside the standard range but within the tolerance limits require no corrective action with respect to the element in question. However, if such inaccuracies are encountered frequently it may indicate that process controls should be reviewed and possibly tightened.

4.2 Construction inaccuracies falling outside the tolerance limits in principal strength members may cause problems in service or may lead to excessive costs at subsequent stages of construction, and may require corrective action. Deviations exceeding the tolerance limits may be considered on a case by case basis, depending on location and extent of the deviation, and the intended service and criticality of the affected element.

4.3 Standard corrective action will be indicated in this guide where appropriate. In other cases appropriate corrective actions may depend on circumstances. (See also Fig. 6 and Fig. 7.)

5. Keywords

5.1 construction tolerances; fit criteria; hull construction; steel hull; strength requirements; tolerance limits

¹ This guide is under the jurisdiction of ASTM Committee F-25 on Ships and Marine Technology and is the direct responsibility of Subcommittee F25.01 on Structures.

Current edition approved Aug. 15, 1994. Published October 1994. Originally published as F 1053 – 87. Last previous edition F 1053 – 87.

Legend:

A Welding

A-1 *Shape of Bead:*

- A-1.1 Undercut (butt weld)
- A-1.2 Undercut (fillet weld)

B Fabrication and Forming

B-1 *Flanged Plate Longitudinal:*

- B-1.1 Breadth of flange
- B-1.2 Height of longitudinal
- B-1.3 Angle between flange and web
- B-1.4 Straightness in the plane of the flange
- B-1.5 Straightness in the plane of the web

B-2 *Flanged Bracket:*

- B-2.1 Breadth of flange
- B-2.2 Angle between flange and web

B-3 *Built-Up Sections:*

- B-3.1 Frame and Longitudinals:
 - B-3.1.1 Deviation from design curvature
 - B-3.1.2 Gap between template and formed section
 - B-3.1.3 Angular deviation of face plate

B-4 *Plates:*

- B-4.1 Cylindrical structures (hast post, etc.)
- B-4.2 Curved shell plate

C Alignment and Fitting

C-1 *Fitting Accuracy:*

- C-1.1 Flange in T longitudinals
- C-1.2 Alignment of intercostal joint
- C-1.3 Gap between beam and frame
- C-1.4 Lap joint
- C-1.5 Alignment of butt joint

C-2 *Openings or entrances:*

- C-2.1 Steel door opening (watertight)

D Distortion and fairness

D-1 *Fairness:*

- D-1.1 General fairness of plating
 - D-1.1.1 Fig. 1
 - D-1.1.2 Fig. 2

D-2 *Distortion of Hull Form:*

- D-2.1 Flatness of Keel

D-3 *Miscellaneous:*

- D-3.1 Permissible distortion of beams, frames, girders and stiffeners
- D-3.2 Permissible warping
- D-3.3 Distortion of H pillar between decks
- D-3.4 Distortion of tripping bracket and small stiffener bracket without faceplate

A. Welding



A-1 Shape of Bead	Tolerance Limits, mm (in.)	Corrective Action
A-1.1 Undercut (butt weld) 	$d = 0.8$ ($1/32$) NOTE—Continuous undercut in thin members (≤ 12.5 mm ($1/2$ in.)) may require special consideration to assure adequate net section.	Repair using small electrode to fill in undercut.
A-1.2 Undercut (fillet weld) 	$d = 0.8$ ($1/32$) NOTE—Continuous undercut in thin members (≤ 12.5 mm ($1/2$ in.)) may require special consideration to assure adequate net section.	Repair using small electrode to fill in undercut.

FIG. 1 Hull Construction Tolerances