



Designation: F1216 – 22

Standard Practice for Rehabilitation of Existing Pipelines and Conduits by the Inversion and Curing of a Resin-Impregnated Tube^{1,2}

This standard is issued under the fixed designation F1216; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This practice describes the procedures for the reconstruction of pipelines and conduits (2 in. to 108 in. diameter) by the installation of a resin-impregnated, flexible tube which is inverted into the existing conduit by use of a hydrostatic head or air pressure. The resin is cured by circulating hot water, introducing controlled steam within the tube, or by photoinitiated reaction. When cured, the finished pipe will be continuous and tight-fitting. This reconstruction process is used in a variety of gravity and pressure applications such as sanitary sewers, storm sewers, process piping, electrical conduits, and ventilation systems.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* For specific precautionary statements, see 7.4.2.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recom-*

mendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:³

D543 Practices for Evaluating the Resistance of Plastics to Chemical Reagents

D638 Test Method for Tensile Properties of Plastics

D790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials

D903 Test Method for Peel or Stripping Strength of Adhesive Bonds

D1600 Terminology for Abbreviated Terms Relating to Plastics

D3567 Practice for Determining Dimensions of “Fiberglass” (Glass-Fiber-Reinforced Thermosetting Resin) Pipe and Fittings

D3839 Guide for Underground Installation of “Fiberglass” (Glass-Fiber Reinforced Thermosetting-Resin) Pipe

D5813 Specification for Cured-In-Place Thermosetting Resin Sewer Piping Systems

E797/E797M Practice for Measuring Thickness by Manual Ultrasonic Pulse-Echo Contact Method

F412 Terminology Relating to Plastic Piping Systems

2.2 AWWA Standard:⁴

M 28 Rehabilitation of Water Mains, Third Ed.

2.3 NASSCO Standard:⁵

Sewer Pipe Cleaning Specification Guideline

3. Terminology

3.1 Definitions are in accordance with Terminology F412 and abbreviations are in accordance with Terminology D1600, unless otherwise specified.

¹ This practice is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.67 on Trenchless Plastic Pipeline Technology.

Current edition approved Aug. 15, 2022. Published August 2022. Originally approved in 1989. Last previous edition approved 2021 as F1216 – 21. DOI: 10.1520/F1216-22.

² The following report has been published on one of the processes: Driver, F. T., and Olson, M. R., “*Demonstration of Sewer Relining by the Insituform Process, Northbrook, Illinois*,” EPA-600/2-83-064, Environmental Protection Agency, 1983. Interested parties can obtain copies from the Environmental Protection Agency or from a local technical library.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

⁴ Available from American Water Works Association (AWWA), 6666 W. Quincy Ave., Denver, CO 80235, <http://www.awwa.org>.

⁵ Available from the National Association of Sewer Service Companies, 5285 Westview Drive, Suite 202, Frederick, MD 21703. <http://www.nassco.org/>

*A Summary of Changes section appears at the end of this standard

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *cured-in-place pipe (CIPP)*—a hollow cylinder containing a nonwoven or a woven material, or a combination of nonwoven and woven material surrounded by a cured thermosetting resin. Plastic coatings may be included. This pipe is formed within an existing pipe. Therefore, it takes the shape of and fits tightly to the existing pipe.

3.2.2 *inversion*—the process of turning the resin-impregnated tube inside out by the use of water pressure or air pressure.

3.2.3 *lift*—a portion of the CIPP that has cured in a position such that it has pulled away from the existing pipe wall.

3.2.4 *photoinitiated reaction*—the polymerization of a resin system initiated by light or other electromagnetic radiation.

4. Significance and Use

4.1 This practice is for use by designers and specifiers, regulatory agencies, owners, and inspection organizations who are involved in the rehabilitation of conduits through the use of a resin-impregnated tube inverted through the existing conduit. As for any practice, modifications may be required for specific job conditions.

5. Materials

5.1 *Tube*—The tube shall consist of one or more layers of flexible needled felt or an equivalent nonwoven or woven material, or a combination of nonwoven and woven materials, capable of carrying resin, withstanding installation pressures and curing temperatures. The tube and any non-structural plastic coating or flexible membrane included in the tube construction shall be compatible with the resin system used. The material shall be able to stretch to fit irregular pipe sections and negotiate bends. The tube shall be fabricated to a size that, when installed, will tightly fit the internal circumference and the length of the original conduit. Allowance shall be made for circumferential stretching during inversion.

5.2 *Resin*—A general purpose, unsaturated, styrene-based, thermoset resin and catalyst system or an epoxy resin and hardener that is compatible with the inversion process shall be used. The resin must be able to cure in the presence of water and the initiation temperature for cure should be less than 180 °F (82.2 °C). The CIPP system shall be expected to have as a minimum the initial structural properties given in [Table 1](#). These physical strength properties shall be determined in accordance with [Section 8](#).

TABLE 1 CIPP Initial Structural Properties^A

Property	Test Method	Minimum Value	
		psi	(MPa)
Flexural strength	D790	4500	(31)
Flexural modulus	D790	250 000	(1724)
Tensile strength (for pressure pipes only)	D638	3000	(21)

^AThe values in [Table 1](#) are for field inspection. The purchaser should consult the manufacturer for the long-term structural properties.

6. Design Considerations

6.1 *General Guidelines*—The design thickness of the CIPP is largely a function of the condition of the existing pipe. Design equations and details are given in [Appendix X1](#).

7. Installation

7.1 Cleaning and Inspection:

7.1.1 Prior to entering access areas such as manholes, and performing inspection or cleaning operations, an evaluation of the atmosphere to determine the presence of toxic or flammable vapors or lack of oxygen must be undertaken in accordance with local, state, or federal safety regulations.

7.1.2 *Cleaning of Pipeline*—All internal debris that will interfere with the installation or adversely affect the performance of the CIPP shall be removed from the original pipeline. Gravity pipes are cleaned with hydraulically powered equipment, high-velocity jet cleaners, mechanically powered equipment, or other applicable method(s) (see NASSCO Sewer Pipe Cleaning Specification Guideline). Pressure pipelines are cleaned with cable-attached devices, fluid-propelled devices, or other applicable method(s) (see Chapter 3 “Pipe Cleaning Methods” in AWWA, M 28 Rehabilitation of Water Mains, Third Ed.).

7.1.3 *Inspection of Pipelines*—Inspection of pipelines shall be performed by experienced personnel trained in locating breaks, obstacles, and service connections by closed-circuit television or worker entry. The interior of the pipeline shall be carefully inspected to determine the location of any conditions that may prevent proper installation of the impregnated tube, such as protruding service taps, collapsed or crushed pipe, and reductions in the cross-sectional area of more than 40 %. These conditions shall be noted and corrected prior to installation of CIPP.

7.1.4 *Line Obstructions*—The original pipeline shall be clear of obstructions such as solids, dropped joints, protruding service connections, crushed or collapsed pipe, and reductions in the cross-sectional area of more than 40 % to ensure proper installation of the resin-impregnated tube. If inspection reveals an obstruction that cannot be removed by conventional sewer cleaning equipment, then a point repair excavation shall be made to uncover and remove or repair the obstruction prior to the installation of the CIPP.

7.2 *Resin Impregnation*—The tube shall be vacuum-impregnated with resin (wet-out) under controlled conditions. The volume of resin used shall be sufficient to fill all the void space present in the tube material at nominal thickness and diameter. The volume shall be adjusted by adding excess resin for the change in resin volume due to polymerization and to allow for any migration of resin into the cracks and joints in the original pipe.

NOTE 1—In pipelines 8 in. diameter and less, 5 % to 10 % excess resin should be added.

7.3 *Bypassing*—If bypassing of the flow is required around the sections of pipe designated for reconstruction, the pump and bypass lines shall be of adequate capacity and size to handle the flow. Services within this reach will be temporarily out of service.