



Designation: F1713 – 08 (Reapproved 2021)^{ε1}

Standard Specification for Wrought Titanium-13Niobium-13Zirconium Alloy for Surgical Implant Applications (UNS R58130)¹

This standard is issued under the fixed designation F1713; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—X2.2 was updated editorially in December 2021.

1. Scope

1.1 This specification covers the chemical, mechanical, and metallurgical requirements for wrought titanium-13niobium-13zirconium alloy to be used in the manufacture of surgical implants (1).²

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:³

- E8/E8M Test Methods for Tension Testing of Metallic Materials
- E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E1409 Test Method for Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by Inert Gas Fusion
- E1447 Test Method for Determination of Hydrogen in Titanium and Titanium Alloys by Inert Gas Fusion Thermal Conductivity/Infrared Detection Method
- E1941 Test Method for Determination of Carbon in Refrac-

tory and Reactive Metals and Their Alloys by Combustion Analysis

E2371 Test Method for Analysis of Titanium and Titanium Alloys by Direct Current Plasma and Inductively Coupled Plasma Atomic Emission Spectrometry (Performance-Based Test Methodology)

F748 Practice for Selecting Generic Biological Test Methods for Materials and Devices

F1472 Specification for Wrought Titanium-6Aluminum-4Vanadium Alloy for Surgical Implant Applications (UNS R56400)

2.2 Aerospace Material Specification:⁴

AMS 2249 Chemical Check Analysis Limits, Titanium and Titanium Alloys

2.3 American Society for Quality (ASQ) Standard:⁵

ASQ C1 Specifications of General Requirements for a Quality Program

2.4 ISO Standards:⁶

ISO 5832-3 Implants for Surgery—Metallic Materials—Part 3: Wrought Titanium 6-Aluminium 4-Vanadium Alloy

ISO 6892 Metallic Materials Tensile Testing at Ambient Temperature

ISO 9001 Quality Management Systems—Requirements

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *beta transus, n*—the minimum temperature at which the alpha-plus-beta phase can transform to 100 % beta phase.

3.1.2 *capability-aged, adj*—the condition of the material that is obtained if, following solution treatment, a sample of the mill product is subjected to an aging treatment such as given below, for certification testing.

3.1.2.1 Age for 6 ± 0.25 h at 923 ± 25 °F (495 ± 14 °C).

¹ This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.12 on Metallurgical Materials.

Current edition approved Dec. 1, 2021. Published December 2021. Originally approved in 1996. Last previous edition approved in 2013 as F1713 – 08 (2013). DOI: 10.1520/F1713-08R21E01.

² The boldface numbers in parentheses refer to the list of references at the end of this standard.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

⁵ Available from American Society for Quality (ASQ), 600 N. Plankinton Ave., Milwaukee, WI 53203, <http://www.asq.org>.

⁶ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

3.1.2.2 Remove from furnace and air cool to room temperature.

3.1.3 *cold work, n*—any mechanical deformation process performed below the recrystallization temperature which results in strain hardening of the material.

3.1.4 *hot work, n*—any mechanical deformation process performed above the recrystallization temperature.

3.1.5 *lot, n*—the total number of mill products produced from the same melt heat under the same conditions at essentially the same time.

3.1.6 *solution-treated, adj*—the condition of the material that is obtained if, following the final hot-working or cold-working operation, the mill product is rapidly quenched, for example, by water quenching, from a temperature above 1112 °F (600 °C).

3.1.7 *unannealed, adj*—the condition of the material that is obtained after the normal hot-working or cold-working operation used for fabrication of the mill product. There are no subsequent heat treatment requirements.

4. Product Classification

4.1 *Bar*—Rounds or flats from 0.188 in. (4.76 mm) to 4 in. (101.6 mm), inclusive, in diameter or thickness. (Other sizes and shapes by special order.)

4.2 *Wire*—Rounds or flats less than 0.188 in. (4.76 mm) in diameter or thickness.

5. Ordering Information

5.1 Include with inquiries and orders for material under this specification the following information:

- 5.1.1 Quantity (weight or number of pieces);
- 5.1.2 Applicable ASTM designation and year of issue;
- 5.1.3 Form (wire or bar, see Section 4);
- 5.1.4 Condition (see 6.2);
- 5.1.5 Mechanical properties (if applicable, for special conditions) (see 8.1);
- 5.1.6 Finish (see 6.1);
- 5.1.7 Applicable dimensions including size, diameter, thickness (for rectangular wire), or print number;
- 5.1.8 Special tests (if any); and
- 5.1.9 Other requirements.

6. Materials and Manufacture

6.1 *Finish*—The mill product may be supplied as specified by the purchaser with a descaled or pickled, abrasive blasted, chemically milled, ground, machined, peeled, or polished finish. On bars, it is permissible to remove minor surface imperfections by grinding if the resultant area meets the dimensional and surface finish requirements of this specification.

6.2 *Condition*—Material shall be furnished in the unannealed, solution-treated, or capability-aged condition, as specified in the purchase order. Conditions and mechanical properties other than those listed in Table 3 may be established by agreement between the supplier and the purchaser.

TABLE 1 Chemical Requirements

Element	Composition (% mass/mass)
Nitrogen, max	0.05
Carbon, max	0.08
Hydrogen, max	0.012 ^A
Iron, max	0.25
Oxygen, max	0.15
Niobium	12.5–14.0
Zirconium	12.5–14.0
Titanium ^B	balance

^A Material 0.032 in. (0.813 mm) and under may have hydrogen content up to 0.015 %.

^B The percentage of titanium is determined by difference and need not be determined or certified.

TABLE 2 Product Analysis Tolerance^A

Element	Tolerance Under the Minimum or Over the Maximum Limit (% mass/mass) ^B
Nitrogen	0.02
Carbon	0.02
Hydrogen	0.0020
Iron	0.10
Oxygen	0.02
Niobium	0.30
Zirconium	0.40

^A Refer to AMS 2249.

^B Under the minimum limit not applicable for elements where only a maximum percentage is indicated.

TABLE 3 Mechanical Properties^{A,B}

Condition	Tensile Strength min, psi (MPa)	Yield Strength (0.2 % offset), min psi (MPa)	Elongation min, % ^C	Reduction of Area min, % ^D
Capability aged	125 000 (860)	105 000 (725)	8	15
Solution treated	80 000 (550)	50 000 (345)	15	30
Unannealed	80 000 (550)	50 000 (345)	8	15

^A Up to 4 in. (101.60 mm) inclusive diameter.

^B Solution treated or unannealed material is not intended for use as a final product without subsequent hot working or heat treatment, or both.

^C Limits apply to tests taken both longitudinal and transverse to the direction of rolling. Elongation of material 0.063 in. (1.575 mm) or greater in diameter (D) or thickness (T) shall be measured using a gage length of 2 in. or 4D or 4T. The gage length shall be reported with the test results. The method for determining elongation of material under 0.063 in. (1.575 mm) in diameter or thickness may be negotiated. Alternately, a gage length corresponding to ISO 6892 may be used when agreed upon between the supplier and purchaser. (5.65 square root S_o, where S_o is the original cross sectional area.)

^D Applies to bar only.

7. Chemical Requirements

7.1 The heat analysis shall conform to the chemical composition of Table 1. Ingot analysis may be used for reporting all chemical requirements, except hydrogen. Samples for hydrogen shall be taken from the finished mill product. The supplier shall not ship material with chemistry outside the requirements specified in Table 1.