



Standard Practice for Infiltration and Exfiltration Acceptance Testing of Installed Corrugated High Density Polyethylene and Polypropylene Pipelines¹

This standard is issued under the fixed designation F2487; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This practice covers procedures for testing installed non-perforated, gasketed corrugated high-density polyethylene (HDPE) and corrugated polypropylene (PP) pipelines using either water infiltration or exfiltration acceptance limits to demonstrate the integrity via the level of leakage of the installed materials, construction procedures and installation quality via the level of leakage. Pipe to be tested under this practice shall include corrugated HDPE and PP drainage pipe meeting the requirements of Specifications **F2306/F2306M**, **F2763**, **F2764/F2764M**, **F2881/F2881M** and **F2947/F2947M**.

NOTE 1—The performance criteria specified in this standard may be used for other plastic pipe products. The engineer, however, must assess if the testing procedures are adequate for the particular material and installation being considered.

NOTE 2—The user of this practice is advised that test criteria presented in this practice are similar to those in general use. Pipe, 600 mm (24 in.) diameter or larger, may be accepted by visual inspection when testing for infiltration.

1.2 This test method shall be performed on lines after all connections and service laterals have been plugged and braced adequately to withstand the test pressures. The time between completion of the backfill operations and testing shall be specified by the approving authority.

1.3 *Units*—The values stated in SI units are to be regarded as standard. The values given in parentheses after SI units are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standard-*

ization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

D3212 Specification for Joints for Drain and Sewer Plastic Pipes Using Flexible Elastomeric Seals

F412 Terminology Relating to Plastic Piping Systems

F2306/F2306M Specification for 300 mm to 1500 mm [12 in. to 60 in.] Annular Corrugated Profile-Wall Polyethylene (PE) Pipe and Fittings for Non-Pressure Gravity-Flow Storm Sewer and Subsurface Drainage Applications

F2763 Specification for 12 to 60 in. [300 to 1500 mm] Dual and Triple Profile-Wall Polyethylene (PE) Pipe and Fittings for Sanitary Sewer Applications

F2764/F2764M Specification for 6 to 60 in. [150 to 1500 mm] Polypropylene (PP) Corrugated Double and Triple Wall Pipe and Fittings for Non-Pressure Sanitary Sewer Applications

F2881/F2881M Specification for 12 to 60 in. [300 to 1500 mm] Polypropylene (PP) Dual Wall Pipe and Fittings for Non-Pressure Storm Sewer Applications

F2947/F2947M Specification for 150 to 1500 mm [6 to 60 in.] Annular Corrugated Profile-Wall Polyethylene (PE) Pipe and Fittings for Sanitary Sewer Applications

3. Terminology

3.1 *Definitions*—For definitions of terms relating to plastic pipe, see Terminology **F412**.

4. Summary of Practice

4.1 Determine the groundwater conditions surrounding the section of pipeline to be tested and select the type of test to be conducted.

¹ This practice is under the jurisdiction of ASTM Committee **F17** on Plastic Piping Systems and is the direct responsibility of Subcommittee **F17.20** on Joining.

Current edition approved Dec. 1, 2021. Published February 2022. Originally approved in 2006. Last previous edition approved in 2017 as F2487–13(2017). DOI: 10.1520/F2487-21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.