



Designation: F2547 – 18 (Reapproved 2023)

Standard Test Method for Determining the Attenuation Properties in a Primary X-ray Beam of Materials Used to Protect Against Radiation Generated During the Use of X-ray Equipment¹

This standard is issued under the fixed designation F2547; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method establishes procedures for measuring the attenuation of X-rays by protective materials at accelerating potentials from 60 to 130 kVp.

1.2 This test method provides attenuation values of primary beam X-radiation.

1.3 This test method applies to both leaded and non-leaded radiation protective clothing materials.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

F1494 Terminology Relating to Protective Clothing

3. Terminology

3.1 Definitions:

3.1.1 *attenuation, n*—for radiological protective material, the reduction in the intensity of the X-ray beam resulting from the interactions between the X-ray beam and the protective material that occur when the X-ray beam passes through the protective material.

¹ This test method is under the jurisdiction of ASTM Committee F23 on Personal Protective Clothing and Equipment and is the direct responsibility of Subcommittee F23.70 on Radiological Hazards.

Current edition approved June 1, 2023. Published June 2023. Originally approved in 2006. Last previous edition approved in 2018 as F2547 – 18. DOI: 10.1520/F2547-18R23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.1.1 *Discussion*—In this test method, the attenuation is calculated as 1 minus the ratio of the measured exposure with a protective material in the beam to the measured exposure without the protective material in the beam at a specific accelerating potential. Multiplying the resulting value by 100 gives percent attenuation.

$$\text{Attenuation (percent)} = \left(1 - \frac{\text{exposure with sample}}{\text{exposure without sample}} \right) \times 100 \quad (1)$$

3.1.2 *coefficient of variation, n*—the ratio of the standard deviation of a sample to the sample mean.

3.1.3 *exposure, n*—for radiological purposes, the amount of ionization in air at standard conditions caused by interaction with X-rays, expressed in units of Roentgen (R) or milliroentgen (mR). The SI units are Coulomb per kilogram (C/kg). 1 Roentgen = 2.58×10^{-4} C/kg.

3.1.4 *half-value layer (HVL), n*—the thickness of aluminum, in millimetres (commonly designated mmAl), that reduces the intensity of the X-ray beam by one half.

3.1.4.1 *Discussion*—The HVL is dependent on the energy of the X-ray beam and, therefore, is different for X-rays produced at different accelerating potentials.

3.1.5 *ionization chamber, n*—a device that measures the electrical charge liberated during the ionization of air molecules by electromagnetic radiation (X-rays for the purposes of this test method), expressed in units of coulombs per kilogram of air.

3.1.6 *kilovolts, peak (kVp), n*—the maximum electrical potential across an X-ray tube during an exposure, expressed in kilovolts.

3.1.7 *lead equivalency, n*—for radiological protective material, the thickness in millimetres of lead (commonly designated mmPb) of greater than 99.9 % purity that provides the same attenuation as a given protective material.

3.1.7.1 *Discussion*—This test method provides the attenuation of the material and not the lead equivalency. Determining lead equivalency would require testing lead of known thickness and purity, and comparing the attenuation of the protective material with the attenuation of the lead. The lead equivalency may be determined based on published half or tenth thickness

values. When lead equivalency is stated, the source of published values shall be stated as the basis of calculation.

$$X = \ln\left(\frac{I}{I_o}\right) / -\mu_{en} \quad (2)$$

where:

X = Pb equivalency,

I/I_o = attenuation (fraction) = incident intensity/transmitted intensity, and

μ_{en} = Pb energy absorption coefficient at test energy, cm^{-1} .

3.1.8 *scatter radiation, n*—a form of secondary radiation resulting from the interaction of the primary X-ray beam and the target (for example, protective material being tested or a patient undergoing a medical procedure).

3.1.9 *secondary radiation, n*—radiation outside the primary X-ray beam.

3.1.10 *shielding, n*—for radiological purposes, any material or obstruction that attenuates radiation to protect personnel or equipment from the effects of ionizing radiation.

3.1.11 *wave form ripple, n*—for radiological purposes, the peak-to-peak variation in the output voltage of the X-ray generator.

3.2 For definitions of other terms related to protective clothing used in this test method, refer to Terminology [F1494](#).

4. Summary of Test Method

4.1 A primary X-ray beam with a standardized energy spectrum and constant intensity is configured to pass through the test setup. An ionization chamber, calibrated for the energy range of X-rays produced at accelerating potentials between 60 to 130 kVp, is used to measure the exposure in the primary beam with and without the material specimen positioned between the X-ray source and the ionization chamber. The exposure is directly proportional to the intensity of the X-ray beam. The attenuation provided by the material specimen is defined as the percentage of the original beam intensity that is removed by the material specimen.

4.2 The attenuation of the sample is determined at an X-ray energy in the range produced by an accelerating potential from 60 to 130 kVp.

5. Significance and Use

5.1 This test method is intended to provide a standardized test procedure of protective materials to ensure comparable results among manufacturers and users.

5.2 This test method involves measurement of the attenuation of X-rays by protective clothing material at an accelerating potential (kVp) between 60 and 130 kVp. These energies are considered to be representative of those commonly used during medical diagnosis.

5.3 The reporting of the attenuation at a specific X-ray energy is intended to allow the end user organization to assess the attenuating properties of the protective clothing material at that energy level.

6. Apparatus

6.1 *Primary X-ray Beam Source*—A variable power, high-frequency X-ray generator coupled with X-ray tube equipped with Tungsten anode with the following characteristics:

6.1.1 The wave form ripple does not exceed 3 %.

6.1.2 The coefficient of variation for the exposure does not exceed 0.05 as determined using four consecutive exposures.

6.1.3 The coefficient of variation for kVp does not exceed 0.05 determined using four consecutive test measurements at the kVp setting used in testing.

6.2 An invasive or non-invasive kVp measuring device capable of measuring the kVp accuracy within 0.5 kVp.

6.3 An ionization chamber and electrometer capable of measuring from 1 mR to 5 R.

6.4 Shielding material may be used around apparatus to improve precision.

7. Hazards

7.1 All individuals performing tests using this test method shall wear X-ray protective clothing or be positioned behind stationary shielding when the X-ray beam is activated.

7.2 All individuals performing tests using this test method shall be monitored for radiation exposure by wearing personal dosimetry commensurate with the testing facilities' radiation safety programs.

8. Sampling and Test Specimens

8.1 Test specimens may come from protective material sheets or from protective material obtained from garments.

8.1.1 Specimens may be single sheets or multiple sheets tested as a stack, as appropriate for the application. When multiple sheets are tested as a stack, the stack should be as flat as possible and air voids between single sheets should be minimized to the extent practical.

8.2 Randomly select a total of five specimens from the material or protective clothing sample for evaluation.

8.3 Test specimens shall have a sufficient area for testing, that is, be large enough to fully intercept the area of the X-ray field at the location of placement of the test specimens.

9. Preparation of Apparatus

9.1 Measure and document the kVp accuracy for each kVp setting used in the testing prior to every testing session.

9.1.1 If the length of the testing session exceeds 1 h, measure and document kVp accuracy at least once each hour.

9.2 Measure and document the exposure reproducibility of the combination of tube current and exposure time used in the testing prior to every testing session.

9.3 Measure and document HVL for the kVp setting used in the testing at the beginning of the testing session.

9.4 Measure and document the kVp accuracy for the kVp setting used in the testing at the end of the testing session.