



Designation: F2986 – 23

Standard Specification for Corrugated Polyethylene Pipe and Fittings for Mine Leachate, Heap Leach Aeration and Other Mining Applications¹

This standard is issued under the fixed designation F2986; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers requirements and test methods for materials, workmanship, dimensions, perforations, pipe stiffness, elongation, joint separation resistance, quality of extruded polyethylene, brittleness, testing, and marking of corrugated polyethylene (PE) pipe and fittings for mine drainage, leachate collection, heap leach aeration, and transmission pipe. It covers nominal sizes 50 mm (2 in.) to 250 mm (10 in.) in single-wall profile, and 75 mm (3 in.) to 1500 mm (60 in.) in double-wall profile.

1.2 This specification covers single profile wall, annular extruded corrugated polyethylene pipe as depicted in Fig. 1, and double wall, annular extruded corrugated polyethylene pipe as depicted in Fig. 2.

1.3 The values stated in SI units are to be regarded as standard. The values given in parentheses are mathematical conversions to inch-pound units that are provided for information only and are not considered standard.

1.4 *The following precautionary caveat pertains only to the test method portion, Section 9, of this specification: This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This test method is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.65 on Land Drainage.

Current edition approved Nov. 1, 2023. Published December 2023. Originally approved in 2012. Last previous edition approved in 2023 as F2986–12(2023). DOI: 10.1520/F2986-23.

2. Referenced Documents

2.1 ASTM Standards:²

- D618 Practice for Conditioning Plastics for Testing
- D1600 Terminology for Abbreviated Terms Relating to Plastics
- D2122 Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings
- D2412 Test Method for Determination of External Loading Characteristics of Plastic Pipe by Parallel-Plate Loading
- D2444 Practice for Determination of the Impact Resistance of Thermoplastic Pipe and Fittings by Means of a Tup (Falling Weight)
- D3350 Specification for Polyethylene Plastics Pipe and Fittings Materials
- D3895 Test Method for Oxidative-Induction Time of Polyolefins by Differential Scanning Calorimetry
- F412 Terminology Relating to Plastic Piping Systems
- F2136 Test Method for Notched, Constant Ligament-Stress (NCLS) Test to Determine Slow-Crack-Growth Resistance of HDPE Resins or HDPE Corrugated Pipe

2.2 ISO Standards:³

- ISO 9969 Thermoplastics pipes —Determination of ring stiffness

3. Terminology

3.1 *Definitions*—Definitions used in this specification are in accordance with Terminology F412 and abbreviations are in accordance with Terminology D1600, unless otherwise specified. The abbreviation for polyethylene is PE.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *crease*—a deformation that cannot be removed like a dent: generally associated with wall buckling.

3.2.2 *leaching*—minerals are removed (leached) from ores that have been mined, crushed, and placed on impervious pads

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from International Organization for Standardization (ISO), ISO Central Secretariat, Chemin de Blandonnet 8, CP 401, 1214 Vernier, Geneva, Switzerland, <https://www.iso.org>.

*A Summary of Changes section appears at the end of this standard




FIG. 1 Typical Single Wall Profile Cross-Section




FIG. 2 Typical Double Wall Profile Cross-Section

for removal (by chemical leaching) by percolation of the solution through the ore, and collection of that solution at the bottom of the heap leach pile.

3.2.3 *NID*, *n*—numerical designation, which is approximately equal to the nominal inside diameter by which a pipe or fitting is defined.

3.2.4 *SN*, *n*—numerical designation of the ring stiffness of the pipe or fitting, determined according to ISO 9969, which is a convenient round number, indicating the minimum required ring stiffness of the pipe or stiffness of the fitting.

3.2.5 *split*—any break or crack that extends through the wall.

4. Ordering Information

4.1 Orders for product made to this specification shall include the following information to adequately describe the desired product:

- 4.1.1 This ASTM designation and year of issue,
- 4.1.2 *Perforations*:
 - 4.1.2.1 With perforations,
 - 4.1.2.2 Without perforations,
- 4.1.3 Diameters,
- 4.1.4 Total footage of each pipe diameter involved,
- 4.1.5 Pipe laying length,
- 4.1.6 *Fitting type(s)*:
 - 4.1.6.1 Size and type of fittings, including mainline and branch diameters, and
 - 4.1.6.2 Number of fittings per diameter.

5. Significance and Use

5.1 Corrugated PE pipe and fittings in this standard are intended for deep underground applications under harsh chemical exposure from a corrosive effluent where they serve as leachate or aeration pipe under a mine heap or dump leaching process. Their major use is to collect or convey ore leachate to a facility for processing and extraction of the desired metal or mineral or to aerate the pile to improve the chemical extraction

of the desired metal by the leachate. Heap leaching is used to extract copper, gold, lead, nickel, silver, uranium, or zinc. The solution is either acidic or alkaline, depending on the metal being extracted.

6. Materials

6.1 *Pipe and Fittings*—The pipe and fittings shall be made of virgin PE plastic compound meeting the requirements of Specification [D3350](#) cell classification 435400C or 435400E.

6.2 The carbon black content shall be equal to or greater than 2.0 % but not exceed 3.0 %. Compounds that have a higher cell classification in one or more performance properties shall be permitted if all other product requirements are met.

6.3 For slow crack-growth resistance, resins shall be evaluated using the notched constant ligament stress (NCLS) test according to the procedure described in [9.13](#). Samples shall be taken from the extruded pipe supplied to the project. The average failure time of the five test specimens shall exceed 24 h with no single test specimen's failure time less than 17 h.

6.4 Samples taken from the extruded pipe supplied to the project shall have a minimum Oxidative-Induction-Time of 20 minutes when tested in accordance with Test Method [D3895](#).

6.5 *Rework Material*—Clean rework material, generated from the manufacturer's own production of this product, may be used by the manufacturer provided that the tubing and fittings produced meet all requirements of this specification.

7. General Requirements

7.1 *Workmanship*—The pipe and fittings shall be homogeneous throughout and be as uniform as commercially practical in color, opacity, and density. The pipe walls shall be free of cracks, holes, blisters, voids, foreign inclusions, or other defects that are visible to the naked eye and that affect the wall integrity. The ends shall be cut cleanly and squarely. Holes intentionally placed in perforated pipe are acceptable.