



Designation: F436/F436M – 24

## Standard Specification for Hardened Steel Washers Inch and Metric Dimensions<sup>1</sup>

This standard is issued under the fixed designation F436/F436M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

### 1. Scope\*

1.1 This specification covers the chemical, mechanical, and dimensional requirements for hardened steel washers for use with fasteners having nominal thread diameters of ¼ through 4 in. and M12 through M100. These washers are intended for general-purpose mechanical and structural use with bolts, nuts, studs, and other internally and externally threaded fasteners. These washers are suitable for use with fasteners covered in Specifications [A354](#), [A449](#), [A563](#), [A563M](#), [F959/F959M](#), and [F3125](#).

1.2 The washers are designated by *type* denoting the material, by *style* denoting the shape, and by inch or metric dimensions.

1.2.1 The types of washers covered are:

1.2.1.1 *Type 1*—Carbon steel.

1.2.1.2 *Type 3*—Weathering steel.

1.2.1.3 This specification provides for furnishing Type 3 to chemical composition or a Corrosion Index (CRI) of 6 or higher at the suppliers option.

1.2.2 The styles of washers covered are:

1.2.2.1 *Circular*—Circular washers in nominal sizes ¼ through 4 in. and M12 through M100 suitable for applications where sufficient space exists and angularity permits.

1.2.2.2 *Beveled*—Beveled washers are square or rectangular, in nominal sizes ½ through 1½ in., M12 through M16, with a beveled 1 to 6 ratio surface for use with American standard beams and channels.

1.2.2.3 *Clipped*—Clipped washers are circular or beveled for use where space limitations necessitate that one side be clipped.

1.2.2.4 *Extra Thick*—Extra thick washers are circular washers in nominal sizes ½ through 4 in., with a nominal thickness of ⅝ in. suitable for structural applications with oversized holes.

1.3 Terms used in this specification are defined in Terminology [F1789](#) unless otherwise defined herein.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee [F16](#) on Fasteners and is the direct responsibility of Subcommittee [F16.06](#) on Steel Washers and Rivets.

Current edition approved Nov. 1, 2024. Published November 2024. Originally approved in 1976. Last previous edition approved in 2019 as F436/F436M – 19. DOI: 10.1520/F0436\_F0436M-24.

1.4 The values stated in either inch-pound units for inch fasteners and SI units for metric fasteners and are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[A354](#) Specification for Quenched and Tempered Alloy Steel Bolts, Studs, and Other Externally Threaded Fasteners

[A449](#) Specification for Hex Cap Screws, Bolts and Studs, Steel, Heat Treated, 120/105/90 ksi Minimum Tensile Strength, General Use

[A563](#) Specification for Carbon and Alloy Steel Nuts (Metric) [A0563\\_A0563M](#)

[A563M](#) Specification for Carbon and Alloy Steel Nuts (Metric) (Withdrawn 2021)<sup>3</sup>

[A588/A588M](#) Specification for High-Strength Low-Alloy Structural Steel, up to 50 ksi [345 MPa] Minimum Yield Point, with Atmospheric Corrosion Resistance

[A751](#) Test Methods and Practices for Chemical Analysis of Steel Products

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [www.astm.org/contact](http://www.astm.org/contact). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

\*A Summary of Changes section appears at the end of this standard



**A1059** Specification for Zinc Alloy Thermo-Diffusion Coatings (TDC) on Steel Fasteners, Hardware, and Other Products

**B695** Specification for Coatings of Zinc Mechanically Deposited on Iron and Steel

**F606/F606M** Test Methods for Determining the Mechanical Properties of Externally and Internally Threaded Fasteners, Washers, Direct Tension Indicators, and Rivets

**F959/F959M** Specification for Compressible-Washer-Type Direct Tension Indicators for Use with Structural Fasteners, Inch and Metric Series

**F1136/F1136M** Specification for Zinc/Aluminum Corrosion Protective Coatings for Fasteners

**F1470** Practice for Fastener Sampling for Specified Mechanical Properties and Performance Inspection

**F1789** Terminology for F16 Mechanical Fasteners

**F2329** Specification for Zinc Coating, Hot-Dip, Requirements for Application to Carbon and Alloy Steel Bolts, Screws, Washers, Nuts, and Special Threaded Fasteners

**F3125** Specification for High Strength Structural Bolts and Assemblies, Steel and Alloy Steel, Heat Treated, Inch Dimensions 120 ksi and 150 ksi Minimum Tensile Strength, and Metric Dimensions 830 MPa and 1040 MPa Minimum Tensile Strength

**G101** Guide for Estimating the Atmospheric Corrosion Resistance of Low-Alloy Steels

### 3. Ordering Information

3.1 Orders for hardened steel washers under this specification shall include the following:

3.1.1 ASTM designation and year of issue,

3.1.2 Quantity (number of pieces by size),

3.1.3 Type and Style (see 1.2.1 and 1.2.2),

3.1.3.1 Material type of washer (that is, Type 1 or Type 3),

3.1.3.2 When the type is not specified, either Type 1 or Type

3 washers may be supplied.

3.1.4 Coating type, if required (see 4.3),

3.1.4.1 When atmospheric corrosion resistance is required, Type 3 washers shall be specified by the purchaser.

3.1.5 Dimensions, nominal size, and other dimensions, if modified from those covered in this specification,

3.1.5.1 Standard thickness shall be supplied unless extra thick is specified.

3.1.6 Specify if inspection at point of manufacture is required,

3.1.7 Specify if test reports are required (see Section 13), and

3.1.8 Any Special or Supplementary requirements, including Surface Roughness (S1).

### 4. Materials and Manufacture

4.1 Steel used in the manufacture of washers shall be produced by the open-hearth, basic-oxygen, or electric-furnace process.

4.2 Washers up to and including 1½ in. for inch fasteners and M36 for metric fasteners, shall be through hardened. Washers over 1½ in. for inch fasteners and M36 for metric

fasteners, may be either through hardened or carburized at the option of the manufacturer.

#### 4.3 Protective Coatings:

4.3.1 Unless otherwise specified, washers shall be furnished “plain” with the “as-fabricated” surface finish without protective coatings.

4.3.2 When zinc-coated washers are required, the purchaser shall specify the zinc coating process, for example, hot-dip, mechanically deposited, Zinc/Aluminum Corrosion Protective Coating, or no preference.

4.3.2.1 When hot-dip is specified the washers shall be zinc coated by the hot-dip process in accordance with the requirements of Specification **F2329**.

NOTE 1—Applying a zinc coating to washers by the hot-dip galvanizing process can cause washers to bond to each other, resulting in a potential for bare (uncoated) surfaces, low coating thicknesses, and workmanship concerns. Suitable acceptance criteria should be agreed upon between the supplier and the purchaser at the time of ordering.

4.3.2.2 When thermo-diffusion is specified the washers shall be zinc coated by the thermo-diffusion process in accordance with the requirements of Class 25 of Specification **A1059**.

4.3.2.3 When mechanically deposited is specified the washers shall be zinc coated by the mechanical-deposition process in accordance with the requirements of Class 55 of Specification **B695**.

4.3.2.4 When Zinc/Aluminum Corrosion Protective Coating is specified, the washers shall be coated in accordance with the requirements of Grade 3 of Specification **F1136/F1136M**.

4.3.3 When the zinc coating process is not specified, the supplier may furnish zinc coated washers in accordance with the supplier’s choice of process from 4.3.2.1 through 4.3.2.4.

4.4 If washers are heat treated by a subcontractor, they shall be returned to the manufacturer for testing prior to shipment to the purchaser.

### 5. Chemical Composition

5.1 Type 1 washers shall conform to the chemical composition specified in **Table 1**.

5.2 Type 3 washers shall conform to the heat analysis specified in **Table 1**. Alternatively, at the suppliers option, Type 3 washers having a Copper minimum Heat Analysis of 0.25%, Phosphorous and Sulfur conforming to **Table 1** and a Corrosion Index of 6 or higher as calculated from the Heat Analysis as described in Guide **G101** Predictive method based on the data of Larabee and Coburn shall be accepted.

5.3 For Type 1 and 3 furnished to the Chemical Compositions in **Table 1**, Product Analysis may be made by the purchaser on finished washers representing each lot. The Chemical Composition shall conform to the requirements in **Table 1**, Product Analysis.

5.4 Product Analysis are not applicable to Type 3 washers furnished to a CRI of 6 or higher calculated from the Heat Analysis.

5.5 Chemical analyses shall be performed in accordance with Test Methods, Practices, and Terminology **A751**.