



Designation: F467 – 24 (Reapproved 2026)

Standard Specification for Nonferrous Nuts for General Use¹

This standard is issued under the fixed designation F467; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers the requirements for commercial wrought nonferrous nuts 0.250 to 1.500 in. inclusive in diameter in a number of alloys in common use and intended for general service applications.

1.2 Applicable bolts, cap screws, and studs for use with nuts covered by this specification are covered by Specification **F468**.

1.3 Terms used in this specification are defined in Terminology **F1789** unless otherwise defined herein.

1.4 The values stated in inch-pound units are to be regarded as standard. No other units of measurement are included in this standard.

NOTE 1—This specification is the inch-pound companion to Specification F467M; therefore, no SI equivalents are presented in the specification.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- B154** Test Method for Mercurous Nitrate Test for Copper Alloys
- E29** Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E34** Test Methods for Chemical Analysis of Aluminum and

- Aluminum-Base Alloys (Withdrawn 2017)³
- E38** Methods for Chemical Analysis of Nickel-Chromium and Nickel-Chromium-Iron Alloys (Withdrawn 1989)³
- E53** Test Method for Determination of Copper in Unalloyed Copper by Gravimetry (Withdrawn 2022)³
- E54** Test Methods for Chemical Analysis of Special Brasses and Bronzes (Withdrawn 2002)³
- E55** Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition
- E62** Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods) (Withdrawn 2010)³
- E75** Test Methods for Chemical Analysis of Copper-Nickel and Copper-Nickel-Zinc Alloys (Withdrawn 2010)³
- E76** Test Methods for Chemical Analysis of Nickel-Copper Alloys (Withdrawn 2003)³
- E101** Test Method for Spectrographic Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique (Withdrawn 1996)³
- E120** Test Methods for Chemical Analysis of Titanium and Titanium Alloys (Withdrawn 2003)³
- E165/E165M** Practice for Liquid Penetrant Testing for General Industry
- E227** Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique (Withdrawn 2002)³
- E354** Test Methods for Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys
- E478** Test Methods for Chemical Analysis of Copper Alloys
- E1409** Test Method for Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by Inert Gas Fusion
- F468** Specification for Nonferrous Bolts, Hex Cap Screws, Socket Head Cap Screws, and Studs for General Use
- F606/F606M** Test Methods for Determining the Mechanical Properties of Externally and Internally Threaded Fasteners, Washers, Direct Tension Indicators, and Rivets
- F812/F812M** Specification for Surface Discontinuities of Nuts, Inch and Metric Series

¹ This specification is under the jurisdiction of ASTM Committee **F16** on Fasteners and is the direct responsibility of Subcommittee **F16.04** on Nonferrous Fasteners.

Current edition approved March 1, 2026. Published March 2026. Originally approved in 1976. Last previous edition approved in 2024 as F467 – 24. DOI: 10.1520/F0467-24R26.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.



F1470 Practice for Fastener Sampling for Specified Mechanical Properties and Performance Inspection

F1789 Terminology for F16 Mechanical Fasteners

2.2 *ASME Standards*:⁴

B 1.1 Unified Inch Screw Threads (UN and UNR and UNJ Thread Forms)

B 18.2.2 Nuts for General Applications: Machine Screw Nuts; and Hex, Square, Hex Flange and Coupling Nuts (Inch Series)

Alloy	Condition
Copper (all alloys)	As formed or stress relieved at manufacturer's option
Nickel alloys 400 and 405	As formed or stress relieved at manufacturer's option
Nickel alloy 500	Solution annealed and aged
Aluminum alloys:	
2024-T4	Solution treated and naturally aged
6061-T6	Solution treated and artificially aged
6262-T9	Solution treated, artificially aged, and cold worked
Titanium	As formed
625	Annealed

4.2.3 *Stress Relieving*—When required, stress relieving shall be specified by the purchaser for all copper alloys and nickel alloys 400 and 405.

5. Chemical Composition

5.1 *Chemical Composition*—The nuts shall conform to the chemical composition specified in **Table 1** for the specified alloy.

5.2 *Manufacturer's Analysis*:

5.2.1 Except as provided in 5.2.2, when test reports are required on the inquiry or purchase order (3.1.8), the manufacturer shall make individual analyses of randomly selected finished nuts from the product to be shipped and report the results to the purchaser. Alternatively, if heat and lot identities have been maintained, the analysis of the raw material from which the nuts have been manufactured may be reported instead of product analysis.

5.2.2 For aluminum nuts, instead of 5.2.1, the manufacturer may furnish a certificate of conformance certifying compliance with the chemical composition specified in **Table 1**.

5.3 *Product Analysis*:

5.3.1 Product analyses may be made by the purchaser from finished products representing each lot. The chemical composition thus determined shall conform to the requirements in **Table 1**.

5.3.2 In the event of disagreement, a referee chemical analysis of samples from each lot shall be made in accordance with 12.1 and 13.1.

6. Mechanical Properties

6.1 The nuts shall be tested in accordance with the mechanical testing requirements for the applicable type and shall meet the mechanical requirements in **Table 2** for the specified alloy.

6.2 Where both proof load and hardness tests are performed, the proof load test results shall take precedence for acceptance purposes.

7. Dimensions

7.1 *Nuts*—Unless otherwise specified, the dimensions of nuts shall be in accordance with the requirements of ASME B18.2.2.

7.2 *Threads*—Unless otherwise specified, the nuts shall have UN Class 2B threads in accordance with ASME B1.1.

3. Ordering Information

3.1 Orders for nuts under this specification shall include the following information:

- 3.1.1 Quantity (number of pieces of each item and size);
- 3.1.2 Name of item (for example, hex nut, heavy hex nut, hex flange nut, jam nut (7.1));
- 3.1.3 Size (diameter, threads per inch, thread form and class (7.2));
- 3.1.4 Alloy number (**Table 1**) and Grade (if required, **Table 2**);
- 3.1.5 Stress relieving, if required (4.2.3);
- 3.1.6 “Shipment lot” testing, as required (Section 9);
- 3.1.7 Source inspection, if required (Section 14);
- 3.1.8 Certificate of compliance or test report, if required (Section 16);
- 3.1.9 Additional requirements, if any, to be specified on the purchase order (4.2.1, 7.2, 8.2, 12.1, and 13.1),
- 3.1.10 Supplementary requirements, if any; and
- 3.1.11 ASTM designation (including year or published date).

NOTE 2—A typical ordering description is as follows: 10 000 pieces, Hex Nut, 0.250" -20UNJC-2B, Alloy Ni59, Grade 2, Furnish Certificate of Compliance, Supplementary Requirement S 3, ASTM Specification F467-XX.

4. Materials and Manufacture

4.1 *Materials*:

4.1.1 The nuts shall be manufactured from material having a chemical composition conforming to the requirements in **Table 1** and capable of developing the required mechanical properties for the specified alloy in the finished fastener in **Table 2**.

4.1.2 The starting condition of the raw material shall be at the discretion of the fastener manufacturer but shall be such that the finished products conform to all the specified requirements.

4.2 *Manufacture*:

4.2.1 *Forming*—Unless otherwise specified, the nuts shall be hot pressed, cold formed, or machined from suitable material at the option of the manufacturer.

4.2.2 *Condition*—Except as provided in 4.2.3, the nuts shall be furnished in the condition specified below:

⁴ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, <http://www.asme.org>.