



Designation: G110 – 92 (Reapproved 2022)^{ε2}

Standard Practice for Evaluating Intergranular Corrosion Resistance of Heat Treatable Aluminum Alloys by Immersion in Sodium Chloride + Hydrogen Peroxide Solution¹

This standard is issued under the fixed designation G110; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Replaced Terminology G15 with Terminology G193, and other editorial changes made throughout in Dec. 2022.

^{ε2} NOTE—Footnote 1 and the ^{ε1} NOTE were corrected editorially in January 2023.

1. Scope

1.1 This practice covers the procedures for immersion tests in sodium chloride + hydrogen peroxide solution. It is primarily for tests of wrought heat treatable aluminum alloys (2XXX and 7XXX) but may be used for other aluminum alloys, including castings. It sets forth the specimen preparation procedures and the environmental conditions of the test and the means for controlling them.

1.2 This practice is intended for evaluations during alloy development and for evaluating production where it may serve as a control test on the quality of successive lots of the same material (see MIL-H-6088 and U.S. Federal Test Method Std. 151b). Therefore strict test conditions are stipulated for maximum assurance that variations in results are attributable to lot-to-lot differences in the material being tested.

NOTE 1—This practice does not address sampling or interpretation or significance of results.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This practice is under the jurisdiction of ASTM Committee G01 on Corrosion of Metals and is the direct responsibility of Subcommittee G01.05 on Laboratory Corrosion Tests.

Current edition approved Dec. 1, 2022. Published January 2023. Originally approved in 1992. Last previous edition approved in 2015 as G110–92 (2015). DOI: 10.1520/G0110-92R22E02.

2. Referenced Documents

2.1 ASTM Standards:²

- D1193 Specification for Reagent Water
 - E3 Guide for Preparation of Metallographic Specimens
 - E407 Practice for Microetching Metals and Alloys
 - G1 Practice for Preparing, Cleaning, and Evaluating Corrosion Test Specimens
 - G67 Test Method for Determining the Susceptibility to Intergranular Corrosion of 5XXX Series Aluminum Alloys by Mass Loss After Exposure to Nitric Acid (NAMLT Test)
 - G69 Test Method for Measurement of Corrosion Potentials of Aluminum Alloys
 - G193 Terminology and Acronyms Relating to Corrosion
- ### 2.2 Other Documents:³
- U.S. Military Specification MIL-H-6088 Heat Treatment of Aluminum Alloys
 - U.S. Federal Test Method, Std. No. 151b Method 822.1, Intergranular Corrosion Test for Aluminum Alloys

3. Summary of Practice

3.1 This practice consists of immersing etched test specimens in a sodium chloride + hydrogen peroxide solution for 6 or more hours. After immersion, metallographic sections are examined to determine the extent of intergranular corrosion (see Terminology G193).

4. Significance and Use

4.1 This practice is especially useful for evaluating the adequacy of quenching when performed on material in the as-quenched condition. The practice may also be used to study the effect of subsequent thermal processes (for example, paint

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from DLA Document Services, Building 4/D, 700 Robbins Ave., Philadelphia, PA 19111-5094, <http://quicksearch.dla.mil>.