



Designation: G111 – 21a

Standard Guide for Corrosion Tests in High Temperature or High Pressure Environment, or Both¹

This standard is issued under the fixed designation G111; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide covers procedures, specimens, and equipment for conducting laboratory corrosion tests on metallic materials under conditions of high pressure (HP) or the combination of high temperature and high pressure (HTHP). See 3.2 for definitions of high pressure and temperature.

1.2 The procedures and methods in this guide are applicable for conducting mass loss corrosion, localized corrosion, and electrochemical tests as well as for use in environmentally induced cracking tests that need to be conducted under HP or HTHP conditions.

1.3 The primary purpose for this guide is to promote consistency of corrosion test results. Furthermore, this guide will aid in the comparison of corrosion data between laboratories or testing organizations that utilize different equipment.

1.4 The values stated in SI units are to be regarded as standard. The values given in parentheses after SI units are provided for information only and are not considered standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- E8/E8M Test Methods for Tension Testing of Metallic Materials
- G1 Practice for Preparing, Cleaning, and Evaluating Corrosion Test Specimens
- G4 Guide for Conducting Corrosion Tests in Field Applications
- G5 Reference Test Method for Making Potentiodynamic Anodic Polarization Measurements
- G30 Practice for Making and Using U-Bend Stress-Corrosion Test Specimens
- G31 Guide for Laboratory Immersion Corrosion Testing of Metals
- G34 Test Method for Exfoliation Corrosion Susceptibility in 2XXX and 7XXX Series Aluminum Alloys (EXCO Test)
- G38 Practice for Making and Using C-Ring Stress-Corrosion Test Specimens
- G39 Practice for Preparation and Use of Bent-Beam Stress-Corrosion Test Specimens
- G46 Guide for Examination and Evaluation of Pitting Corrosion
- G49 Practice for Preparation and Use of Direct Tension Stress-Corrosion Test Specimens
- G59 Test Method for Conducting Potentiodynamic Polarization Resistance Measurements
- G78 Guide for Crevice Corrosion Testing of Iron-Base and Nickel-Base Stainless Alloys in Seawater and Other Chloride-Containing Aqueous Environments
- G106 Practice for Verification of Algorithm and Equipment for Electrochemical Impedance Measurements
- G129 Practice for Slow Strain Rate Testing to Evaluate the Susceptibility of Metallic Materials to Environmentally Assisted Cracking
- G170 Guide for Evaluating and Qualifying Oilfield and Refinery Corrosion Inhibitors in the Laboratory

¹ This guide is under the jurisdiction of ASTM Committee G01 on Corrosion of Metals and is the direct responsibility of Subcommittee G01.05 on Laboratory Corrosion Tests.

Current edition approved Nov. 1, 2021. Published December 2021. Originally approved in 1992. Last previous edition approved in 2021 as G111 – 21. DOI: 10.1520/G0111-21A.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

G184 Practice for Evaluating and Qualifying Oil Field and Refinery Corrosion Inhibitors Using Rotating Cage

G185 Practice for Evaluating and Qualifying Oil Field and Refinery Corrosion Inhibitors Using the Rotating Cylinder Electrode

G193 Terminology and Acronyms Relating to Corrosion

G208 Practice for Evaluating and Qualifying Oilfield and Refinery Corrosion Inhibitors Using Jet Impingement Apparatus

3. Terminology

3.1 *Definitions*—The definitions of terms given in Terminology **G193** shall be considered as applying to this guide.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *high temperature and high pressure, HTHP, n*—for the purpose of this guide, any combination of pressure and temperature that requires the use of an autoclave.

3.2.2 *effectively non-reactive, adj*—free of significant mass loss or localized corrosion, stress corrosion cracking (SCC), or other embrittlement phenomena in the test environment; not contaminate the test environment with corrosion or other reaction products; and not significantly consume, absorb, or adsorb reactive chemical species from the test environment.

3.3 *Abbreviations and Acronyms:*

3.3.1 *AI*—artificial intelligence

3.3.2 *ALARP*—as low as reasonably practicable

3.3.3 *CUE*—corrosion under excursions

3.3.4 *HV*—high velocity

3.3.5 *ML*—machine learning

3.3.6 *PVT*—pressure volume temperature

3.3.7 *RT*—radiography testing (X-ray)

3.3.8 *SCC*—stressed-corrosion cracking

3.3.9 *SME*—subject matter expert

3.3.10 *UT*—ultrasonic testing

4. Summary of Guide

4.1 This guide describes the use of corrosion coupons, stress corrosion cracking specimens, and electrochemical electrodes in HP and HTHP environments. It also includes guidelines for the use of high-pressure test cells with these specimens to obtain reproducible, accurate corrosion test data.

4.2 Typically, HP and HTHP tests involve exposure of test specimens to a liquid (aqueous or non-aqueous), gaseous or multiphase environment, or both, in an appropriate test cell. The test cell shall be able to resist corrosion and cracking (mechanical and environmental) in the test environment while containing the pressurized, heated environment. Furthermore, the test specimens in the HP or HTHP test, or both, can be exposed in either stressed or unstressed condition in either the free corroding state or under electrochemical polarization.

5. Significance and Use

5.1 Autoclave tests are commonly used to evaluate the corrosion performance of metallic and non-metallic materials

under simulated HP and HTHP service conditions. Examples of service environments in which HP and HTHP corrosion tests have been used include chemical processing, petroleum production and refining, food processing, pressurized cooling water, electric power systems, and aerospace propulsion.

5.2 For the applications of corrosion testing listed in 5.1, the service environment involves handling corrosive and potentially hazardous media under conditions of high pressure or high temperature, or both. The temperature and pressure, among other parameters, usually drive the composition and properties of the aqueous phase and, hence, the severity of the corrosion process. Consequently, the laboratory evaluation of corrosion severity cannot be performed in conventional low pressure glassware without making potentially invalid assumptions as to the potential effects of high temperature and pressure on corrosion severity.

5.3 Therefore, there is a substantial need to provide standardized methods by which corrosion testing can be performed under HP and HTHP. In many cases, however, the standards used for exposure of specimens in conventional low-pressure glassware experiments cannot be followed due to the limitations of access, volume, and visibility arising from the construction of high-pressure test cells. This guide refers to existing corrosion standards and practices, as applicable, and then goes further in areas in which specific guidelines for performing HP and HTHP corrosion testing are needed.

6. Apparatus

6.1 *Test Cell:*

6.1.1 Shall be constructed to applicable standards and codes so that it will have an adequate pressure rating to handle the test pressure safely.

6.1.2 Shall be made of materials that are corrosion resistant and effectively non-reactive with the test environment.

6.1.3 Shall have a seal mechanism that can withstand both the pressures, temperatures, and corrosive environment to be used in the test. Periodic hydrostatic testing of the test cell is recommended to ensure pressure retaining capabilities.

6.1.4 Shall be designed to have the necessary inlet and outlet ports to allow the test environment to be established in a controllable manner, monitored and sampled during the exposure period, released in a controlled manner at the completion of the test, and, if over temperature or pressure conditions may occur, adequate over pressure release and over temperature control equipment should be used.

6.2 *Test Cell Feedthroughs:*

6.2.1 Should be designed to minimize frictional forces when external loading fixtures are used for stressing specimens.

6.2.2 May be designed to balance the internal pressure in the test vessel with the external stressing assembly.

6.2.3 Shall be designed so that the electrodes or stressing rods and specimens cannot be ejected from the test cell under pressure.

6.2.4 Shall provide the electrical isolation of the specimen from the test cell unless galvanic coupling is specifically desired.