



Designation: G22 – 23

Standard Practice for Determining Resistance of Plastics to Bacteria¹

This standard is issued under the fixed designation G22; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ε) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This practice covers two procedures, A and B, for determining the effect of bacteria on the properties of plastics in the form of molded and fabricated articles, tubes, rods, sheets, and film materials. Procedure B provides a more extensive contact between the test bacteria and the specimens than does Procedure A. Changes in optical, mechanical, and electrical properties may be determined by the applicable ASTM methods.

1.2 The values stated in SI units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D618 Practice for Conditioning Plastics for Testing

G21 Practice for Determining Resistance of Synthetic Polymeric Materials to Fungi

3. Summary of Practice

3.1 The procedure described herein consists of the following steps:

¹ This practice is under the jurisdiction of ASTM Committee G03 on Weathering and Durability and is the direct responsibility of Subcommittee G03.04 on Biological Deterioration.

Current edition approved Feb. 1, 2023. Published February 2023. Originally approved in 1976. Last previous edition approved in 1996 as G22 – 76 (1996) which was withdrawn January 2002 and reinstated in February 2023. DOI: 10.1520/G0022-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.1 Selection of suitable specimens for determination of pertinent properties,

3.1.2 Inoculation of specimens with suitable organisms,

3.1.3 Exposure of inoculated specimens under conditions favorable to growth,

3.1.4 Examination and rating for visual growth, and

3.1.5 Removal, sterilization, and evaluation of specimens.

NOTE 1—Since the procedure involves handling and working with bacteria that may be capable of infecting man, it is essential that personnel trained in microbiology perform the portion of the procedure involving handling of bacterial organisms and inoculated specimens.

4. Significance and Use

4.1 The resin portion of plastic materials is usually resistant to bacteria, in that it does not serve as a carbon source for the growth of bacteria. It is generally the other components, such as plasticizers, lubricants, stabilizers, and colorants that are responsible for bacterial attack on plastic materials. It is important to establish the resistance of plastics to microbial attack when plastics are used under conditions of high temperature and humidity favorable for such attack.

4.2 The effects to be expected are:

4.2.1 Surface attack, discoloration, and loss of transmission (optical).

4.2.2 Removal of susceptible plasticizers, modifiers, and lubricants, resulting in increased modulus (stiffness), changes in weight, dimensions, and other physical properties, and deterioration of electrical properties such as insulation resistance, dielectric constant, power factor, and dielectric strength.

4.3 Often the changes in electrical properties are due principally to surface growth and associated moisture, and to pH changes caused by products of bacterial metabolism. Other effects include preferential growths caused by nonuniform dispersion of plasticizers, lubricants, and other processing additives. Pronounced physical changes may be observed on products in film form or as coatings where the ratio of surface to volume is high, and where nutrient materials such as plasticizers and lubricants continue to diffuse to the surface as they are utilized by the organisms.

4.4 Since attack by organisms involves a large element of change due to local accelerations and inhibitions, the order of reproducibility may be rather low. To assure that estimates of