



INTERNATIONAL STANDARD ISO 5627:1995 TECHNICAL CORRIGENDUM 1

Published 2002-06-15

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Paper and board — Determination of smoothness (Bekk method)

TECHNICAL CORRIGENDUM 1

Papier et carton — Détermination du lissé (Méthode Bekk)

RECTIFICATIF TECHNIQUE 1

Technical Corrigendum 1 to International Standard ISO 5627:1995 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 2, *Test methods and quality specifications for paper and board*.

Page 3, subclause 5.1

Insert the following paragraph after note 1:

If there is a bevel on the inner edge of the glass plate, the inside diameter is measured across the top edge of the bevel and is equal to $11,3 \text{ mm} \pm 0,05 \text{ mm}$. If no bevel is present on the inner edge, the inside diameter of the glass plate shall be $11,3 \text{ mm} \pm 0,05 \text{ mm}$, as shown in Figure 2.