

ISO

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION

ISO RECOMMENDATION

R 600

PLASTICS

DETERMINATION OF THE VISCOSITY RATIO OF POLYAMIDES IN CONCENTRATED SOLUTION

1st EDITION

August 1967

COPYRIGHT RESERVED

The copyright of ISO Recommendations and ISO Standards belongs to ISO Member Bodies. Reproduction of these documents, in any country, may be authorized therefore only by the national standards organization of that country, being a member of ISO.

For each individual country the only valid standard is the national standard of that country.

Printed in Switzerland

Also issued in French and Russian. Copies to be obtained through the national standards organizations.

BRIEF HISTORY

The ISO Recommendation R 600, *Plastics – Determination of the viscosity ratio of polyamides in concentrated solution*, was drawn up by Technical Committee ISO/TC 61, *Plastics*, the Secretariat of which is held by the United States of America Standards Institute (USASI).

Work on this question by the Technical Committee began in 1960 and led, in 1961, to the adoption of a Draft ISO Recommendation.

This first Draft ISO Recommendation (Nº 513) was circulated in June 1962 to all the ISO Member Bodies for enquiry. As the results of this consultation were not considered satisfactory, the Technical Committee presented a second Draft ISO Recommendation which was circulated to all the Member Bodies in July 1964 and which was approved, subject to a few modifications of an editorial nature by the following Member Bodies:

Austria	India	South Africa
Belgium	Italy	Rep. of
Canada	Japan	Sweden
Chile	Korea, Rep. of	U.A.R.
Czechoslovakia	Netherlands	United Kingdom
Denmark	New Zealand	U.S.A.
Finland	Poland	U.S.S.R.
Germany	Romania	

One Member Body opposed the approval of the Draft:

France

The second Draft ISO Recommendation was then submitted by correspondence to the ISO Council, which decided, in August 1967, to accept it as an ISO RECOMMENDATION.